arXiv:1102.2744v2 [math.CO] 20 Apr 2011

POLYNOMIALS FOR CRYSTAL FRAMEWORKS AND THE RIGID UNIT MODE SPECTRUM

S. C. POWER

Abstract. Two derivations are given for a matrix-valued function $\Phi_{\mathcal{C}}(z)$, defined on the d-torus, that can be associated with a discrete, translationally periodic bar-joint framework $\mathcal{C}$ in $\mathbb{R}^d$. The rigid unit mode (RUM) spectrum of $\mathcal{C}$ is defined in terms of the phases of phase-periodic infinitesimal flexes and is identified in terms of the singular points of the function $z \to \operatorname{rank}\Phi_{\mathcal{C}}(z)$ and also in terms of the wave vectors of excitations with vanishing energy in the long wavelength limit. To a crystal framework $\mathcal{C}$ in Maxwell counting equilibrium we associate a unique multi-variable monic polynomial $p_{\mathcal{C}}(z_1, \dots, z_d)$ and for ideal zeolites the algebraic variety of zeros of $p_{\mathcal{C}}(z)$ on the d-torus determines the RUM spectrum. The matrix function is related to periodic "floppy modes" and their asymptotic order and an explicit formula is obtained for the number of periodic floppy modes for a given supercell. The crystal polynomial, RUM spectrum and the mode multiplicity are computed for a number of fundamental examples. In the case of certain zeolite frameworks in dimensions 2 and 3 direct proofs are give to show the maximal floppy mode property (order N). In particular this is the case for the cubic symmetry sodalite framework and for some novel two-dimensional zeolite frameworks.

1. Introduction

Let $\mathcal{C}$ be a mathematical crystal framework, by which we mean a connected structure in the Euclidean space $\mathbb{R}^d$ consisting of a set $\mathcal{C}_e$ of framework edges (bars or bonds) with a corresponding set $\mathcal{C}_v$ of framework vertices (joints or atoms) such that $\mathcal{C}_e$ is periodic with respect to a discrete translation group $\mathcal{T}$ of isometries of $\mathbb{R}^d$ with full rank. We mainly consider the case $d = 3$ together with the physical locally finite assumption in which $\mathcal{C}_e$ is generated by the translations of a finite set of edges and vertices. Such a geometric bar-joint framework $\mathcal{C}$ serves as a model for the essential geometry of the disposition of atoms and bonds in a material crystal $\mathcal{M}$. In this case the vertices have atomic identifiers, such as H, He, Li, B, ... , and the chosen edges may correspond to the strong bonds. The identification of strongly bonded molecular units, such as SiO_4 and TiO_6, imply a polyhedral net structure for $\mathcal{C}$

2000 *Mathematics Subject Classification.* 52C25, 74N05, 47N50
Key words and phrases: Crystal framework, matrix-valued function, rigidity operator, crystal polynomial, rigid unit mode.

and in particular aluminosilicate crystals and zeolites provide a fascinating diversity of tetrahedral nets in which every vertex is shared by two tetrahedra.

Material scientists are interested in the manifestation and explanation of various forms of low energy motion and oscillation in materials. Of particular interest are the rigid unit modes (RUMs) in crystals and zeolites. These are the low energy (long wavelength) modes of crystal lattice oscillation which are related to the relative motions of rigid units, such as the SiO_4 tetrahedral units in quartz. The wave vectors of these vibrational modes are observed in neutron scattering experiments and have been shown to correlate closely with those for the modes observed in numerical simulations with periodic networks of rigid units. In both the experimental measurements and in the computer simulations the background mathematical model is classical lattice dynamics and the rigid unit modes are observed where phonon dispersion curves display markedly low energy. There is now a considerable body of literature tabulating the rigid unit modes of various crystals and it has become evident that the primary determinant for these low energy modes in a material $\mathcal{M}$ is the geometric structure of its abstract framework $\mathcal{C}$. This work shows that typically the wave vectors of RUMs lie along lines and planes in reciprocal space but there are surprises. Firstly the wave vectors often lie on curved "exotic" surfaces in reciprocal space [4]. Secondly some zeolites have one or more rigid unit mode oscillation for every wave vector, representing an extraordinary degree of flexibility [6], [7]. See also [5] and [21].

As we shall demonstrate the mathematics of rigid unit modes is essentially a linear first order theory and one can side-step much of the lattice dynamical formulations that relate to higher energy phonons and their dispersion curves. This was outlined in the seminal paper of Giddy, Dove, Pawley and Heine [5] and has been pursued effectively in the recent mathematical analysis of Wegner [22].

Motivated partly by material phenomena, in Owen and Power [16] the rigid unit mode spectrum was formally defined for an abstract crystal framework $\mathcal{C}$ with its translation group $\mathcal{T}$ as the set $\Omega = \Omega(\mathcal{C})$ of points $\omega = (\omega_1, \omega_2, \omega_3)$ arising from the nonzero *infinitesimal flexes* u of $\mathcal{C}$ which are $\mathcal{T}$-periodic modulo the phase factor $\omega = (\omega_1, \omega_2, \omega_3)$. Here $\omega_j = \exp(2\pi i k_j)$ and $\mathbf{k} = (k_1, k_2, k_3)$, located in $[0,1) \times [0,1) \times [0,1)$, is the reduced wave vector associated with u. The rigid unit modes of $\mathcal{C}$ are defined to be the infinitesimal flexes u and so one may define the multiplicity of rigid unit modes for the pair $(\mathcal{C}, \mathcal{T})$ with wave vector $\mathbf{k}$ (or phase point ω) as a vector space dimension. See Definitions 2.6, 2.7, 3.2, 4.1.

The infinitesimal flex perspective is useful in that it brings into play the well-established theory of infinitesimal rigidity for finite bar-joint frameworks. We show here that the consideration of general infinitesimal flexes in *infinite bar-joint frameworks* is effective in the analysis of the RUM spectrum. For example the identification of infinitesimal flexes localised to lines and planes (and appropriately partially phase-periodic) leads to planes and lines (respectively) in the RUM spectrum. We also see formally, in Theorem 5.1 that the vector space formulation of rigid unit modes for $\mathcal{C}$ does correspond to the phenomenological appearance of rigid unit modes in materials and in simulations. That is, the phase of a phase-periodic infinitesimal flex corresponds to a wave vector for which the harmonic oscillation excitations of vertices (atoms) have vanishing bond deformations in the infinite wavelength (slow oscillation) limit.

In [16] various flexibility and rigidity properties were considered for abstract crystal frameworks in d dimensions. In the case of square-summable displacement vectors this lead to an associated matrix-valued function defined on the d-torus $\mathbb{T}^d$. This function, $\Phi_{\mathcal{C}}(z)$, arises from a representation of the infinite rigidity matrix for $\mathcal{C}$ as a Hilbert space multiplication operator for a matrix-valued function, known in Toeplitz operator theory as the symbol function. The RUM spectrum $\Omega(\mathcal{C})$ was shown to correspond to the set of points in $\mathbb{T}^d$ where the null-space of $\Phi(z)$ is nontrivial. In the case of periodic tetrahedral nets (mathematical zeolites) this is the set of zeros for the determinant of $\Phi_{\mathcal{C}}(z)$ and the so the RUM spectrum of the crystal framework is identified with the zero set of a multi-variable trigonometric polynomial on $\mathbb{T}^d$ with real coefficients.

In what follows we give two direct derivations of $\Phi_{\mathcal{C}}(z)$ which avoid Hilbert space rigidity operators and we formalise the association of a unique multivariable polynomial with a well-constrained crystal framework. The first derivation is elementary and arises from the identification of the family of matrices that characterise the rigid unit modes as null eigenvectors. The second arises from an explicit block diagonalisation of the finite rigidity matrices associated with supercells and here $\Phi_{\mathcal{C}}(z)$ appears as the "completion" of matrix-valued "functions" on finite subsets of the d-torus. A companion viewpoint to this is that the supercell rigidity matrices associated with fixed period infinitesimal motions are obtained by "sampling" $\Phi_{\mathcal{C}}(z)$ at appropriate rational points of the d-torus.

Using block diagonalisation we analyse the asymptotic order of the number of periodic infinitesimal flexes, or floppy modes, associated with supercells. Also we give an explicit formula for the number of periodic floppy modes associated with an $r_1 \times r_2 \times r_3$ supercell, which resolves a question posed by Simon Guest. This number is computable from the matrix function as the sum

$$\sum_{0\leq k_i<r_i, 1\leq i\leq 3} \dim\ker(\Phi_{\mathcal{C}}(\omega^k))$$

where $k = (k_1, k_2, k_3)$ and $\omega^k = (e^{2\pi i k_1/r_1}, e^{2\pi i k_2/r_2}, e^{2\pi i k_3/r_3})$. We also give a formal proof for a general crystal framework in $\mathbb{R}^d$ that $\mathcal{C}$ is of "order N" if and only if $\Omega(\mathcal{C})$ has dimension d (and hence coincides with $\mathbb{T}^d$). Here "order N" means that with increasing supercell size the number of periodic floppy modes increases as the order of the number N of atoms in the supercell. While it is generally true that in three dimensions, for example, order $N^{2/3}$ (resp. order $N^{1/3}$) is equivalent to RUM dimension 2 (resp. dimension 1) when $\Omega(\mathcal{C})$ is standard, this may be in question if $\Omega(\mathcal{C})$ is exotic and does not admit a rational parametrisation. We also prove, by straightforward linear algebra, that order N is equivalent to the existence of localised floppy modes.

In the final section we compute the rigid unit mode spectrum, the mode multiplicity and the crystal polynomial for various fundamental examples including the frameworks for β-cristobolite, sodalite and perovskite. We give the novelty of a two-dimensional framework with an exotic spectrum. This is defined by the simple requirement that the unit cell consist of an 8-ring of congruent equilateral triangles bordering a regular octagon. Its crystal polynomial $p_{\mathcal{C}}(z, w, u)$ has total degree 6 and two explicit cubic factors which contribute two "figure eight" curves to the spectrum. Also we indicate an approach to exotic curves and surfaces in terms of RUM *spectrum evolutions* in which the spectrum evolve in response to the "phase transition" through a periodicity-preserving framework deformation.

With regard to order N, we show that it is possible for a "two-dimensional zeolite" to have order N, which resolves a problem posed by Mike Thorpe. In three dimensions it has been known from experimental studies that the cubic symmetry form of sodalite exhibits a rigid unit mode for each wave vector. See Dove-et-al [4], [6] where this mode of flexibility is linked to material properties. We provide a direct geometric proof that $\mathcal{C}_{\mathrm{SOD}}$ has a localised infinitesimal flex and so for this reason has order N.

The focus in the sequel is for idealised crystal frameworks and the RUM *spectrum* and mode multiplicity comply with the strict mathematical sense of the definitions. In particular this spectrum is a real algebraic variety. On the other hand material crystals, such as the aluminosilicates surveyed in [4], have a rigid unit mode *distribution* determined experimentally. The accord between some of these sets of wave vectors underlines the efficacy of the rigid unit model as a primary determinant of low energy excitation modes in materials.

The development here, which is self-contained, relates in part to themes and problems discussed at a London Mathematical Society workshop on *The Rigidity of Frameworks and Applications.* [1] We briefly indicate some very recent papers that also address the rigidity and flexibility of periodic structures. On the mathematical side,

---

[1] University of Lancaster, July 2010 (Power [18].)

Borcea and Streinu [1] and Malestein and Theran [13] examine periodic frameworks which are otherwise generic and in particular the latter paper obtains a combinatorial characterisation of periodic infinitesimal rigidity for frameworks in $\mathbb{R}^2$. Ross, Shulze and Whiteley [19], on the other hand, consider periodic frameworks which are rich in symmetry but are otherwise generic and obtain counting conditions for the prediction of finite motions. In Power [17] we derive the Borcea-Streinu rigidity matrix given in [1] and obtain Maxwell-Calladine and Fowler-Guest style equations (see [9], [15], [20]) for periodic frameworks. The flexibility considerations in these four papers are liberal in allowing affine deformation of the (Bravais) lattice structure while maintaining framework periodicity with respect to the deforming lattice. Such flexibility contrasts with the considerations here in which, on the one hand the lattice is fixed, an appropriate constraint for RUM analysis, and on the other hand periodicity for infinitesimal flexes is relaxed to periodicity-modulo-phase. Nevertheless there are interesting connections to explore between these perspectives, such as the analysis of RUM evolutions indicated in Section 5. On the applications side, in addition to the work on RUMs indicated above we note that Kapko, Dawson, Treacy and Thorpe [12] have computed the flexibility windows (related to minimum and maximum volume deformation) of the frameworks of ideal zeolites.

The author is grateful for stimulating discussions and communications with Martin Dove, Simon Guest, John Owen, Mike Thorpe, Franz Wegner and Walter Whiteley.

2. Crystal frameworks and infinitesimal rigidity.

We first define crystal frameworks and their matrix-valued functions and give the main ingredients of infinitesimal flexibility for translationally periodic bar-joint frameworks.

The following notational conventions are adopted. We write κ for the label of a framework vertex in the unit cell, while k denotes a general multi-index $(k_1, \dots, k_d)$ in $\mathbb{Z}^d$ and $\mathbf{k}$ denotes a wave vector, as indicated above.

2.1. **Crystal frameworks and motifs.**

We focus mainly on three-dimensional frameworks since the adaptations needed for the extension to $d = 2, 4, 5, \dots$ are essentially notational. Let $G = (V, E)$ be a countable simple graph with $V = \{v_1, v_2, \dots\}, E \subseteq V \times V$ and let $p_i = p(v_i)$ be corresponding points in $\mathbb{R}^3$. Then the pair (G, p) is said to be a *bar-joint framework* in $\mathbb{R}^3$ with framework vertices, or joints, p_i and framework edges, or bars, given by the straightline segments $[p_i, p_j]$ between p_i and p_j when (v_i, v_j) is an edge in E.

An *isometry* of $\mathbb{R}^3$ is a distance-preserving map $T : \mathbb{R}^3 \to \mathbb{R}^3$. A *full rank translation group* $\mathcal{T}$ is a set of translation isometries $\{T_k : k \in \mathbb{Z}^3\}$

with $T_{k+l} = T_k + T_l$ for all k, l, $T_k \neq I$ if $k \neq 0$ and such that the three vectors

$$a = T_{e_1}0, \quad b = T_{e_2}0, \quad c = T_{e_3}0,$$

associated with the generators $e_1 = (1, 0, 0), e_2 = (0, 1, 0), e_3 = (0, 0, 1)$ of $\mathbb{Z}^3$ are not coplanar.

Definition 2.1. A crystal framework $\mathcal{C}$ in $\mathbb{R}^3$ with full rank translation group $\mathcal{T}$ and finite *motif* (F_v, F_e) is a countable bar-joint framework (G, p) in $\mathbb{R}^3$ with a periodic labelling

$$V = \{v_{\kappa,k} : \kappa \in \{1, \dots t\}, k \in \mathbb{Z}^3\}, \quad p_{\kappa,k} = p(v_{\kappa,k}),$$

such that

(i) $F_v = \{p_{\kappa,0} : \kappa \in \{1, \dots, t\}\}$ and $F_e \subseteq E$ is a set of framework edges with at least one framework vertex in F_v,

(ii) for each κ and n the point $p_{\kappa,n}$ is the translate $T_n p_{\kappa,0}$,

(iii) the set $\mathcal{C}_v$ of all framework vertices is the disjoint union of the sets $T_k(F_v), k \in \mathbb{Z}^3$,

(iv) the set $\mathcal{C}_e$ of all framework edges is the disjoint union of the sets $T_k(F_e), k \in \mathbb{Z}^3$.

The finiteness of the motif and the full rank of $\mathcal{T}$ ensure that $\mathcal{C}_v$ is a countable periodic set. We say that a crystal framework in $\mathbb{R}^3$ is in *Maxwell counting equilibrium* if $3|F_v| = |F_e|$. Of particular interest amongst these are the 6-regular frameworks in which each atom is incident to 6 bonds and this includes the case of tetrahedral nets with each vertex shared by two tetrahedra.

The principle ingredient of a crystal framework $\mathcal{C}$ is the pair $(\mathcal{C}_v, \mathcal{C}_e)$ comprised by the periodic set $\mathcal{C}_e$ of framework edges together with its vertex set $\mathcal{C}_v$. Indeed one may view nonperiodic and quasicrystal frameworks in such terms. With translational periodicity there are choices for the isometry group $\mathcal{T}$, since one may take subgroups, and there are further choices for motifs. It is natural to define the *unit cell* associated with $\mathcal{T}$, and its labelling, as the closed parallelepiped set determined by the vectors a, b, c. However it is also convenient, for notational bookkeeping for the atoms on cell boundaries, to remove three of the faces of the unit cell to ensure no overlapping under translation.

Definition 2.2. The (principal) *partition unit cell* for $(\mathcal{C}, \mathcal{T})$ is the set E of points with vectors $t_1a + t_2b + t_3c, 0 \leq t_i < 1, 1 \leq i \leq 3\}$, that is, the parallelepiped set determined by a, b, c minus the three closed faces which do not contain a pair from $\{a, b, c\}$. A general partition unit cell is an $\mathbb{R}^3$-translate of E.

With E as in the definition it is natural to take F_v as the set $\mathcal{C}_v \cap E$ and to let F_e consist of the edges in E together with some framework edges incident to framework vertices in F_v and satisfying the partitioning property (iv). Also it may be judicious, for symmetry considerations, to translate $\mathcal{C}$ to a "normalised" position so that the set $\mathcal{C}_v \cap E$ acquires certain simplicity or symmetry.

Definition 2.3. A motif (F_v, F_e) is of *incident type* for $\mathcal{C}$ and $\mathcal{E}$ if $F_v = \mathcal{C}_v \cap E = \{p_{\kappa,0} : 1 \leq \kappa \leq t\}$ and if each framework edge e in F_e has the form $e = [p_{\kappa,0}, p_{\tau,\delta(e)}]$ where $\kappa \in F_v$. The index $\delta(e) \in \mathbb{Z}^3$ is the *exponent* of e.

Note that the exponent of e is $(0,0,0)$ if and only if e, as a closed set, is contained in the unit cell E. Thus, the edges in F_e with nonzero exponent have one vertex in the partition unit cell and the other vertex in the $T_{\delta(e)}$-translate of this cell. We may define the

For example, Figure 1 shows such an incident type motif and partition unit cell for the so-called kagome framework $\mathcal{C}_{kag}$ which is formed by corner-linked triangles in a regular hexagonal arrangement. The isometry group $\mathcal{T}$ in this case is generated by the two translations whose period vectors are given by the sides of the boundary of the unit cell.



FIGURE 1. Motif and possible unit cell boundary for the kagome framework, $\mathcal{C}_{kag}$.

On the other hand Figure 2 illustrates a motif for the (rigid) squares grid $\mathcal{C}_{sq}$ made up of corner-linked rigid squares in regular square arrangement. This may be viewed as a $2d$ analogue of the basic octahedron network considered later which underlies the material crystal perovskite. The period vectors can be taken to be $a = (2,0), b = (0,2)$, with $F_v = \{(0,1),(1,0)\}$ for the motif vertices. Note that the edge $e_4 = [p_{2,(0,1)}, p_{1,(1,0)}]$ in $F_e = \{e_1, \ldots, e_5\}$ has both vertices outside the partition unit cell $[0,2) \times [0,2)$. In particular this motif is not of incident type.



FIGURE 2. Unit cell and motif for the squares network, $\mathcal{C}_{sq}$.

2.2. **The function $\Phi_\mathcal{C}(z)$.** We now define the matrix-valued function, or symbol function, for $\mathcal{C}$ that is associated with a given motif (F_v, F_e). Different motifs give matrix functions that are equivalent in the simple manner indicated below.

Write $z = (z_1, \dots, z_d)$, with $z_i \in \mathbb{C}, |z_i| = 1,,$ to denote general points in the d-torus. Typically ω denotes a particular such point, especially a RUM value. Thus, with the usual multinomial convention ω^k may denote the scalar value associated with a RUM point which is the product $\omega_1^{k_i} \dots \omega_d^{k_d}$. On the other hand, just as z^3 is convenient notation to denote the monomial function $z \to z^3$ on $\mathbb{T}$, we write z^k for the monomial function $z \to z^k$ from $\mathbb{T}^d$ to $\mathbb{C}$. Since ${z_i}^{-k} = \overline{z_i}^k$ for points on the circle $\mathbb{T}$ we may think of general monomials z^δ as products of the z_i or $\overline{z}_i$ with just non-negative powers.

The examples we discuss occur in two and three dimension and in this case we dispense with subscripts and write (z, w) and (z, w, u) respectively for general points of $\mathbb{T}^2$ and $\mathbb{T}^3$ respectively.

First we isolate the special case in which the motif is of incident type and has the added restriction that there are no "reflexive" edges of the form $e = [p_{\kappa,0}, p_{\kappa,\delta(e)}]$ in F_e. Note that the edge e_5 in the motif of Figure 2 is of this form. Such *simple* incident type motifs are usually available for the frameworks of material crystals.

The coordinates in $\mathbb{R}^3$ of the point $p_{\kappa,k}$ in $\mathbb{R}^3$ will be written as $(p_{\kappa,1,k}, p_{\kappa,2,k}, p_{\kappa,3,k})$ and also, in the next section, as $(p_{\kappa,x,k}, p_{\kappa,y,k}, p_{\kappa,z,k})$.

Definition 2.4. Let $\mathcal{C}$ be a crystal framework with simple incident type motif (F_v, F_e), with

$$F_v = \{p_{\kappa,0} : 1 \leq \kappa \leq n\}, \quad F_e = \{e_i : 1 \leq i \leq m\}.$$

Then $\Phi_\mathcal{C}(z)$ is the $m \times 3n$ matrix of functions $\phi_{ij}(z)$ on $\mathbb{T}^d$ such that for each edge $e_i = e = [p_{\kappa,0}, p_{\tau,\delta(e)}]$, $1 \leq i \leq m$,

$$\phi_{i,3(\kappa-1)+\sigma}(z) = p_{\kappa,\sigma,0} - p_{\tau,\sigma,\delta(e)},$$

$$\phi_{i,3(\tau-1)+\sigma}(z) = -(p_{\kappa,\sigma,0} - p_{\tau,\sigma,\delta(e)})\bar{z}^{\delta(e_i)},$$

with the remaining entries equal to zero.

The edges in a general motif have two forms, namely nonreflexive or reflexive. The former take the form $e = [p_{\kappa,\delta(e,\kappa)}, p_{\tau,\delta(e,\tau)}]$, with $\kappa \neq \tau$, and with $\delta(e,\kappa)$ and $\delta(e,\tau)$ possibly both nonzero. The "reflexive" edges have the form $[p_{\kappa,\delta_1(e)}, p_{\kappa,\delta_2(e)}]$. We may choose such edges so that $\delta_1 = 0$.

Using a symbolic labelling for columns we now state the general form of $\Phi_{\mathcal{C}}(z)$.

Definition 2.5. Let $\mathcal{C}$ be a crystal framework in $\mathbb{R}^3$ with general motif (F_v, F_e), with

$$F_v = \{p_{\kappa,0} : 1 \leq \kappa \leq n\}, \quad F_e = \{e_i : 1 \leq i \leq m\}.$$

Then $\Phi_{\mathcal{C}}(z)$ is the $m \times 3n$ matrix of functions such that for each edge $e = [p_{\kappa,\delta(e,\kappa)}, p_{\tau,\delta(e,\tau)}]$, with $\kappa \neq \tau$,

$$(\Phi_{\mathcal{C}}(z))_{e,(\kappa,\sigma)} = (p_{\kappa,\sigma,\delta(e,\kappa)} - p_{\tau,\sigma,\delta(e,\tau)})\bar{z}^{\delta(e,\kappa)},$$

$$(\Phi_{\mathcal{C}}(z))_{e,(\tau,\sigma)} = -(p_{\kappa,\sigma,\delta(e,\kappa)} - p_{\tau,\sigma,\delta(e,\tau)})\bar{z}^{\delta(e,\tau)},$$

while for each reflexive edge $[p_{\kappa,0}, p_{\kappa,\delta(e)}]$

$$(\Phi_{\mathcal{C}}(z))_{e,(\kappa,\sigma)} = (p_{\kappa,\sigma,0} - p_{\kappa,\sigma,\delta(e)})(1 - \bar{z}^{\delta(e)}),$$

with the remaining entries in each row equal to zero.

Despite the notational detail above the algorithmic passage from crystal to matrix function is straightforward as we see in the following examples and in Section 5. Note that $\Phi(z)$ may be constructed directly from an associated standard *motif graph* $G(\mathcal{M})$ which we define to be the vertex-labelled graph whose vertex set is $V(F_v)$, the set of *all* vertices of the motif edges, whose edge set is F_e, and whose labelling is given by asigning the k index to each external vertex. For example for the motif of Figure 2, the motif graph is also implied, with the two vertices of e_4 carrying the labels $(1, 0)$ and $(0, 1)$.

In the definition and notation above the dependence of $\Phi_{\mathcal{C}}(z)$ on the motif is straightforward. Replacement of a motif edge (resp. vertex) by a $\mathcal{T}$-equivalent one results in multiplication of the appropriate row (resp. columns) by a monomial. Thus in general two motif matrix functions $\Phi(z)$ and $\Psi(z)$ satisfy

$$\Psi(z) = D_1(z)A\Phi(z)BD_2(z),$$

where $D_1(z), D_2(z)$ are diagonal matrix function with monomial functions on the diagonal and where A, B are permutation matrices, associated with edge and vertex relabelling.

Example (a). Let $\mathcal{C}_{sq}$ be the crystal framework in the plane defined by the motif illustrated in Figure 2. More precisely, with F_v equal to the ordered set $\{(1/2,0),(0,1/2)\}$ and $F_e = \{e_1,\dots,e_5\}$, $\mathcal{C}_{\rm sq}$ is a connected network of rigid squares. It follows from Definition 2.5 that

$$\Phi_{\mathcal{C}_{\rm sq}}(z,w) = \frac{1}{2}\begin{bmatrix} 1 & -1 & -1 & 1 \\ -1 & -1 & \bar{z} & \bar{z} \\ -\bar{w} & -\bar{w} & 1 & 1 \\ -\bar{w} & \bar{w} & \bar{z} & -\bar{z} \\ 0 & 0 & -2+2\bar{z} & 2-2\bar{z} \end{bmatrix}.$$

If the final row of $\Phi_{\mathcal{C}_{\rm sq}}(z,w)$ is deleted then one has the matrix function for the square grid framework, $\mathcal{C}_{\mathbb{Z}^2}$ say. This framework is in Maxwell counting equilibrium and

$$\det \Phi_{\mathcal{C}_{\mathbb{Z}^2}}(z,w) = 4\ (\bar{w}-\bar{z})\,(\bar{w}\bar{z}-1)\,.$$

Example (b)[16]**.** The matricial symbol function of the kagome framework $\mathcal{C}_{\rm kag}$ determined by the six-edged motif of Figure 2 is given by

$$\Phi_{kag}(z,w) = \frac{1}{4}\begin{bmatrix} -2 & 0 & 2 & 0 & 0 & 0 \\ 0 & 0 & 1 & -\sqrt{3} & -1 & \sqrt{3} \\ -1 & -\sqrt{3} & 0 & 0 & 1 & \sqrt{3} \\ 2 & 0 & -2\,z & 0 & 0 & 0 \\ 0 & 0 & -1 & \sqrt{3} & \overline{zw} & -\sqrt{3}\overline{z}w \\ \overline{w} & \sqrt{3}\overline{w} & 0 & 0 & -1 & -\sqrt{3} \end{bmatrix}$$

with determinant equal to a constant multiple of

$$\overline{zw}(z-1)\,(w-1)\,(z-w).$$

2.3. **Polynomials for crystal frameworks.** Let $\mathcal{C}$ be a crystal framework with a given isometry group $\mathcal{T}$. If $\mathcal{C}$ is in Maxwell counting equilibrium, that is, if $d|F_v| = |F_e|$, then we may form the polynomial $\det(\Phi_{\mathcal{C}}(z))$ of the matrix function associated with a particular motif. This is a polynomial in the coordinate functions z_i and their complex conjugates $\overline{z_i}$, that is, a multi-variable trigonometric polynomial on the d-torus. We remove dependence on the motif and formally define the *crystal polynomial* $p_{\mathcal{C}}(z)$, associated with $\mathcal{C}$ and a lexicographic monomial ordering, as the product $z^\gamma \det(\Phi_{\mathcal{C}}(z))$ where γ is chosen so that

(i) $p_{\mathcal{C}}(z)$ is a linear combination of nonnegative power monomials,

$$p_{\mathcal{C}}(z) = \sum_{\alpha\in\mathbb{Z}_+^d} a_\alpha z^\alpha,$$

(ii) $p_{\mathcal{C}}(z)$ has minimum total degree, and
(iii) $p_{\mathcal{C}}(z)$ has leading monomial with coefficient 1.

Here the monomials are ordered lexicographically, so that, for example, the monomial function $z_1^2z_2$ has higher multi-degree than $z_1z_2^3$. It is thus possible to talk of the leading term of a multivariable polynomial

[3]. The crystal polynomial for the kagome framework, with motif and translation group as above is $p_{kag}(z,w) = (z-1)\,(w-1)\,(z-w)$, or, expanded in monomial order, with precedence $z > w > u$,

$$p_{kag}(z,w) = z^2w - z^2 - zw^2 + z + w^2 - w.$$

We see in Section 5 that the factorisation of such polynomials is closely linked to the structure of the RUM spectrum of $\mathcal{C}$.

2.4. **Rigidity matrices and floppy modes.**

Let $\mathcal{C}$ be a crystal framework in $\mathbb{R}^2$ with framework vertices $p_{\kappa,k}$. A *displacement vector* for $\mathcal{C}$ is doubly-indexed sequence u of vectors $u_{\kappa,k}$ in $\mathbb{R}^3$ regarded as a sequence of displacement directions, or instantaneous velocities, assigned to the frameworks vertices $p_{\kappa,k}$. It is convenient to consider the vector space of all real displacement sequences, $u = (u_{\kappa,k})$, written

$$\mathcal{H}_{atom} = \Pi_{\kappa,k}\mathbb{R}^3.$$

Definition 2.6. A real *infinitesimal flex* u for $\mathcal{C}$ is a displacement vector u in $\mathcal{H}_{atom}$ such that

$$\langle u_{\kappa,k} - u_{\tau,l}, p_{\kappa,k} - p_{\tau,l}\rangle = 0$$

for each framework edge $[p_{\kappa,k}, p_{\tau,l}]$.

Thus a infinitesimal flex of $\mathcal{C}$ is an instantaneous atom velocity sequence such that at the two ends of each edge the velocity components in the edge direction are equal. The terminology here, borrowed from finite framework theory, reflects the equivalent formulation which requires that, for all small time t the perturbed edge

$$[p_{\kappa,k} + tu_{\kappa,k}, p_{\tau,l} + tu_{\tau,l}]$$

has length of second order smallness. That is,

$$|[p_{\kappa,k} + tu_{\kappa,k}, p_{\tau,l} + tu_{\tau,l}]| = |p_{\kappa,k} - p_{\tau,l}| + O(t^2)$$

as t tends to zero. Here the implicit constant for $O(t^2)$ depends only on the edge and so, for example, an infinitesimal rotation qualifies as an infinitesimal flex (despite the unbounded nature of the flex sequence.)

The *rigidity matrix* $R(\mathcal{C})$ is an infinite matrix defined exactly as in the finite framework case.

Definition 2.7. The rigidity matrix $R(\mathcal{C})$ of the crystal framework $\mathcal{C}$ has rows labelled by the edges $e = [p_{\kappa,k}, p_{\tau,l}]$, columns labelled by the framework vertex coordinate variables $(\kappa, x, k), (\kappa, y, k), (\kappa, z, k)$, and row e takes the form

$$[\cdots 0\ (p_{\kappa,k} - p_{\tau,l})\ 0 \cdots 0\ (p_{\tau,l} - p_{\kappa,k})\ 0 \cdots]$$

where the entry $(p_{\kappa,k} - p_{\tau,l})$ indicates that the three coordinates of this vector lie in the columns for $(\kappa, x, k), (\kappa, y, k), (\kappa, z, k)$.

We remark that one may take the view that $R(\mathcal{C})$ is $1/2J(\mathcal{C})$ where $J(\mathcal{C})$ is the infinite Jacobian, evaluated at the $p_{\kappa,k}$ for the quadratic equation system

$$|q_{\kappa,k} - q_{\tau,l}|^2 = d_e^2$$

where d_e is the length of the edge e.

It is natural to take a linear algebraic perspective and consider various linear transformations that derive from $R(\mathcal{C})$.

Let

$$\mathcal{H}_{bond} = \Pi_{e\in\mathcal{C}_e}\mathbb{R} = \Pi_{e\in F_e,k\in\mathbb{Z}^2}\mathbb{R}$$

be the space of real sequences $w = (w_{e,k})_{e\in F_e,k\in\mathbb{Z}^3}$ labelled by the framework edges. Then $R(\mathcal{C})$ gives a linear transformation $R : \mathcal{H}_{atom} \to \mathcal{H}_{bond}$. Indeed, each row of R has at most 6 nonzero entries and the image $R(u)$ is given by the well-defined matrix multiplication $R(\mathcal{C})u$. As for finite frameworks one has the following elementary proposition.

Proposition 2.8. *The infinitesimal flexes of $\mathcal{C}$ are the displacement vectors which lie in the nullspace of linear transformation R.*

For $r = (r_1, r_2, r_3)$ in $\mathbb{Z}^3$ let $\mathcal{H}_a^r$ be the finite-dimensional subspace of displacement vectors u for which $u_{\kappa,n+m} = u_{\kappa,n}$ if r_i divides $m_i, 1 \leq i \leq 3$. These vectors can be viewed as the displacements determined by their restriction to the r-fold motif, denoted (F_v^r, F_e^r), for the indexing subgroup $r\mathbb{Z}^3 = r_1\mathbb{Z} \times r_2\mathbb{Z} \times r_3\mathbb{Z}$. It is natural to take F_v^r (resp. F_e^r) to be the union of the disjoint k-indexed translates of F_v (resp. F_e), where $k = (k_1, k_2, k_3), 0 \leq k_i \leq r_i - 1$. Similarly define $\mathcal{H}_b^r$ and note that $R(\mathcal{C})$ provides a linear transformation

$$R^{(r)} : \mathcal{H}_a^r \to \mathcal{H}_b^r$$

of finite-dimensional vector spaces. For example this follows from the commutation relations in Section 3.

In particular, for $r = (1, 1, 1)$ the transformation $R^{(r)}$ is a linear transformation between the spaces of strictly periodic vectors. With respect to the natural basis this transformation provides a rigidity matrix which we denote as $R(\mathcal{M})$ and refer to as the motif rigidity matrix [10], [16].

The following definition accords with the usual usage in applications, where a crystal framework is said to be of order N if the number of periodic floppy modes possessed by a supercell is of the same order as the total degrees of freedom of the vertex atoms in the supercell.

Definition 2.9. Let $\mathcal{C}$ be a crystal framework in $\mathbb{R}^3$ and let $R^{(r)}$ be the finite-dimensional linear transformation induced by $R(\mathcal{C})$ for the n-fold supercell, where $r = (n, n, n)$.

(i) A *floppy mode* or, more precisely, a periodic floppy mode, of $\mathcal{C}$ is a nonzero vector u in the nullspace of $R^{(r)}$ for some $r \in \mathbb{Z}^3$.

(ii) A *local floppy mode* is a nonzero vector $u = (u_{\kappa,k})$ in the nullspace of $R(\mathcal{C})$ which vanishes outside some supercell, that is, $u_{\kappa,k} = 0$ for all but finitely many values k.

(ii) $\mathcal{C}$ is said to be of *order* N^α for floppy modes, where $\alpha = 0, \frac{1}{3}, \frac{2}{3}$ or 1, if for some constant $C > 0$ the nullity $\nu_n = \dim\ker R^{(r)}$ satisfies $\nu_n \geq Cn^{3\alpha}$ for all n, while there is no such constant for the power $\alpha+\frac{1}{3}$. In particular $\mathcal{C}$ is said to be of order N if $\nu_n \geq cn^3$ for some constant $c > 0$.

Note that if $\mathcal{C}$ has a local floppy mode u then by considering disjointly supported translates of u one may obtain linearly independent local floppy modes of order $N = n^3$ in number in an n-fold supercell. Further, these local floppy modes have n-fold periodic floppy modes associated with them and so it follows that $\mathcal{C}$ is of order N in this case.

We now show that the converse implication follows from simple linear algebra

Let us specify notation for the natural "basic sequences" of $\mathcal{H}_{atom}$ and $\mathcal{H}_{bond}$. Write ξ_x, ξ_y, ξ_z for the standard coordinate basis of $\mathbb{R}^3$, $\xi_x = (1, 0, 0)$ etc., and for $\sigma \in \{x, y, z\}$ write $\xi_{\kappa,\sigma,k}$ for the position indicator vector u in $\mathcal{H}_{atom}$ with

$$(\xi_{\kappa,\sigma,k})_{\kappa',\sigma',k'} = \delta_{\kappa,\kappa'}\delta_{\sigma,\sigma'}\delta_{k,k'},$$

where $\delta_{\kappa,\kappa'}$ is the Kronecker delta. While $\mathcal{H}_{atom}$ does not have countable vector space dimension its subspace of finitely nonzero sequences has the set $\{\xi_{\kappa,\sigma,k}\}$ as a vector space basis. Similarly we write $\eta_{e,k}$ for the basic sequence in $\mathcal{H}_{bond}$ which is zero but for the value 1 for the coordinate position e, k.

For the subspaces of r-fold periodic vectors we introduce some analogous notation. Write $k \in r$ to denote an integer points $k = (k_1, k_2, k_3)$ in $\mathbb{Z}^3$ with $0 \leq k_i \leq r_i - 1$. Consider the set

$$\{\dot{\xi}_{\kappa,\sigma,k} : \kappa \in \{1, 2, \ldots, |F_v|\}, \sigma \in \{x, y, z\}, k \in r\},$$

where $\dot{\xi}_{\kappa,\sigma,k}$ is the r-fold periodic vector whose $\kappa', \sigma', 0$ coordinate is $\delta_{\kappa,\kappa'}\delta_{\sigma,\sigma'}$. This is a vector space basis for $\mathcal{H}^r_{atom}$. Also we write

$$\{\dot{\eta}_{e,k} : e \in \{1, 2, \ldots, |F_e|\}, k \in r\}.$$

for the natural basis of $\mathcal{H}^r_{bond}$.

Define the *boundary* F_e^{bdry} of the motif (F_v, F_e) as the set of vertices $V(F_e)\backslash F_v$. For $r = (n, n, n)$ the boundary of the motif (F^r_v, F^r_e) is contained in the union of the boundaries of the motifs for the cells in the boundary of the n-fold supercell. It consists of the points that lie outside the union of the n^3 partition unit cells and in particular $|(F^r_e)^{bdry}| \leq Cn^2$ for some constant C and all n. In the simple case of a rectangular unit cell and an edge motif F_e of *adjacent connection type*, in the sense that the exponent δ_e for e in F_e takes one of the seven forms $(0,0,0),(\pm 1,0,0),(0,\pm 1,0),(0,0,\pm 1)$, one can verify that $|(F_e^r)^{bdry}| = 3n^2|F_e|$ for all $r = (n,n,n)$.

Proposition 2.10. *Let $\mathcal{C}$ be a crystal framework in $\mathbb{R}^3$ which is of order N for floppy modes. Then $\mathcal{C}$ has a local floppy mode.*

Proof. With $r = (n,n,n)$ let P be the linear "boundary projection" transformation on $\mathcal{H}_a^r$ such that $P\dot{\xi}_{\kappa,\sigma,k} = \dot{\xi}_{\kappa,\sigma,k}$ if the pair κ, k label a boundary point of F_e^r in F_v^r and is zero otherwise. The dimension of the "boundary vector space" $P(\mathcal{H}_a^r)$ is equal to $|(F_e^r)^{bdry}|$ and so is of order n^2.

Let $u^1,\dots,u^k$, with $k = \nu_n$, be a basis for the nullspace of $R(\mathcal{C}_n) = R^{(r)}$. Using the assumption, choose n so that $k > \dim P(\mathcal{H}_a^r)$. Thus the k vectors $Pu^1,\dots,Pu^k$ are linearly dependent and for some set of coefficients λ_i, not all of which are zero, we have

$$0 = \lambda_1 Pu^1 + \cdots + \lambda_k Pu^k = P(\lambda_1 u^1 + \cdots + \lambda_k u^k).$$

Also, since $u^1,\dots,u^k$ is a basis the vector $u = \lambda_1 u^1 + \cdots + \lambda_k u^k$ is a nonzero vector in the periodic vector space $\mathcal{H}_a^r$ with $Pu = 0$. Note that such a non zero periodic displacement vector, which is zero on the boundary vertices of the supercell, can be localised by truncation to create the floppy mode u', where $u'_{\kappa,0} = u_{\kappa,0}$ and $u'_{\kappa,k} = 0$ if $k \neq (0,0,0)$. To see explicitly that this truncation is an infinitesimal flex one need only consider the (new) displacements, u'_α, u'_β for the two vertices p_α, p_β of an edge e which has just one vertex, p_β say, in the partition supercell. But in this case the internal vertex has a T_r-translate to a boundary vertex of F_e^r and so by periodicity $u'_\beta = u_\beta = 0$. Thus with the truncation change $u_\alpha \to u'_\alpha = 0$ one still has the infinitesimal flex requirement

$$\langle u'_\alpha - u'_\beta, p_\alpha - p_\beta\rangle = 0$$

□

3. THE ROLE OF $\Phi_{\mathcal{C}}(z)$.

We first show how $\Phi_{\mathcal{C}}(z)$ arises as a family of matrices parametrised by points z in the d-torus where the matrix for $z = \omega$ determines the infinitesimal flexes that are periodic modulo the phase $\overline{\omega}$. Once again, for notational simplicity we assume that $d = 3$.

3.1. **Phase-periodic infinitesimal flexes.** Let $\mathcal{K}_{atom}, \mathcal{K}_{bond}$ be the complex scalar vector spaces $\mathcal{K}_{atom} = \mathbb{C} \otimes \mathcal{H}_{atom}, \mathcal{K}_{bond} = \mathbb{C} \otimes \mathcal{H}_{bond}$. Write $\mathcal{K}_a^\omega$ for the complex vector space of displacement vectors $v = (v_{\kappa,k})$ such that $v_{\kappa,k} = \omega^k v_{\kappa,0}$ for $\kappa \in F_v, k \in \mathbb{Z}^3$. This is a finite-dimensional subspace of $\mathcal{K}_{atom}$ and we similarly define $\mathcal{K}_b^\omega \subset \mathcal{K}_{bond}$.

The matrix $R(\mathcal{C})$ provides a linear transformationn $R^\omega : \mathcal{K}_a^\omega \to \mathcal{K}_b^\omega$ by restriction. Indeed, let $\gamma_i, 1 \leq i \leq 3$, denote the usual generators for

$\mathbb{Z}^3$ and let W_i and U_i be the shift transformations on $\mathcal{K}_{atom}$ and $\mathcal{K}_{bond}$ respectively, with

$$W_i : \xi_{\kappa,\sigma,k} \to \xi_{\kappa,\sigma,k+\gamma_i},$$
$$U_i : \eta_{e,k} \to \eta_{e,k+\gamma_i}.$$

Then we have the commutation relations

$$R(\mathcal{C})W_i = U_i R(\mathcal{C}), \quad 1 \le i \le 3,$$

and the identities $W_i u = \overline{\omega_i} u$, for $u \in \mathcal{K}_a^\omega$, and $U_i v = \overline{\omega_i} v$, for $v \in \mathcal{K}_b^\omega$. Thus for u in $\mathcal{K}_a^\omega$,

$$U_i(R(\mathcal{C})u) = R(\mathcal{C})(W_i u) = R(\mathcal{C})(\overline{\omega_i} u) = \overline{\omega_i} R(\mathcal{C})u$$

and so $R(\mathcal{C})u \in \mathcal{K}_b^\omega$.

Let $\{\xi_{\kappa,\sigma} : \kappa \in F_v, \sigma \in \{x, y, z\}\}$ be the natural basis for the column vector space $\mathbb{C}^{3|F_v|}$. Write $\xi_{\kappa,\sigma}^\omega$ for the displacement vectors in $\mathcal{K}_a^\omega$ which "extend" the basis elements $\xi_{\kappa,\sigma,0}, \kappa \in F_v, \sigma \in \{x, y, z\}$. Formally, in terms of Kronecker delta symbol, we have

$$(\xi_{\kappa,\sigma}^\omega)_{\kappa',\sigma',k} = \delta_{\kappa,\kappa'}\delta_{\sigma,\sigma'}\omega^k.$$

Similarly let $\eta_e, e \in F_e$, be the standard basis for $\mathbb{C}^{|F_e|}$ and write $\eta_e^\omega, e \in F_e$, for the natural associated basis for $\mathcal{K}_b^\omega$, with

$$(\eta_e^\omega)_{e',k} = \omega^k \delta_{e,e'}.$$

Proposition 3.1. *Let $\mathcal{C}$ be a crystal framework with matrix function $\Phi_\mathcal{C}(z)$ and let $\omega \in \mathbb{T}^d$. Then the scalar matrix $\Phi_\mathcal{C}(\overline{\omega})$ is the representing matrix for the linear transformation $R^\omega : \mathcal{K}_a^\omega \to \mathcal{K}_b^\omega$ with respect to the natural bases $\{\xi_{\kappa,\sigma}^\omega\}$ and $\{\eta_e^\omega\}$.*

Proof. Let $\langle \ , \ \rangle$ denote the scalar product in $\mathcal{K}_b^\omega$ for which the natural basis elements are orthonormal, that is, using the Kronecker delta symbol, $\langle \eta_e^\omega, \eta_f^\omega \rangle = \delta_{e,f}$. Then the entry of the representing matrix for R^ω in the e row and the κ', σ column is

$$(R^\omega)_{e,(\kappa',\sigma)} = \langle R(\mathcal{C})\xi_{\kappa',\sigma}^\omega, \eta_e \rangle.$$

From the definition of the rigidity matrix it follows that $R\xi_{\kappa',\sigma}^\omega$ is a sum of phase-periodic vectors provided by the edges e in F_e, with $e = [p_{\kappa,\delta_1}, p_{\tau,\delta_2}]$, where κ' is equal to one, or both, of κ and τ. In fact, using the Kronecker symbol $\delta_{\kappa',\kappa}$, and writing v_e for the edge vector $p_{\kappa,\delta_1} - p_{\tau,\delta_2}$, we have

$$R\xi_{\kappa',\sigma}^\omega = \sum_{e=[p_{\kappa,\delta_1}, p_{\tau,\delta_2}] \in F_e} (\delta_{\kappa',\kappa}\omega^{\delta_1}(v_e)_\sigma - \delta_{\kappa',\tau}\omega^{\delta_2}(v_e)_\sigma)\eta_e^\omega.$$

To see this note that

$$(R(\mathcal{C})\xi_{\kappa',\sigma}^\omega)_{e,0} = \delta_{\kappa',\kappa}(v_e)_\sigma\omega^{\delta_1} - \delta_{\kappa',\tau}(v_e)_\sigma\omega^{\delta_2}.$$

Also $R(\mathcal{C})\xi_{\kappa',\sigma}^\omega$ is ω-periodic and the vectors η_e^ω form a basis for the space of ω-periodic vectors in the range. Thus $R(\mathcal{C})\xi_{\kappa',\sigma}^\omega$, and hence $R^\omega\xi_{\kappa',\sigma}^\omega$, is equal to the sum indicated above.

Noting the form of $\Phi_{\mathcal{C}}(\omega)$ in Definition 2.5 it follows

$$\langle R\xi^{\omega}_{\kappa',\sigma}, \eta^{\omega}_{e}\rangle = (\Phi_{\mathcal{C}}(\overline{\omega}))_{e,(\kappa',\sigma)}.$$

□

The proposition gives a method for finding the RUM spectrum in the sense of the following preliminary definition.

Definition 3.2. Let $\mathcal{C}$ be a crystal framework in $\mathbb{R}^3$ with translation group $\mathcal{T}$. Then the RUM spectrum $\Omega(\mathcal{C})$ for $(\mathcal{C}, \mathcal{T})$ is the set of points ω in $\mathbb{T}^3$ for which there exists a nonzero vector in the nullspace of R^{ω}.

The formalism here is essentially the one adopted by Wegner [22] in his computational determination of exotic RUM spectra. However here we bring the linear space transformations and structures more explicitly into play. We note also that Hutchinson and Fleck [11] in their engineering analysis of kagome related structures adopt a phase-periodic flex and stresses analysis, drawing on the formalism of lattice dynamics and Bloch's theorem. They also make explicit the kagome function matrix.

3.2. $\Phi_{\mathcal{C}}(z)$ **and floppy mode counting.** We now start afresh and derive $\Phi_{\mathcal{C}}(z)$ as the completion of a function defined on the rational points $\omega = (w_1, w_2, w_3)$ with $w_i = e^{2\pi i\alpha_i}$ and α a rational number in the interval $[0, 1)$. Despite the notational density the proof is essentially the matricial form of a standard block diagonalisation argument for transformations that intertwine cyclic shifts.

Let $r = (r_1, r_2, r_3)$ and consider the finite-dimensional space $\mathcal{K}^r_a = \mathcal{H}^r_a \otimes \mathbb{C}$ in $\mathcal{K}_{atom} = \mathcal{H}_{atom} \otimes \mathbb{C}$ consisting of r-periodic complex displacement vectors. This has a basis of vectors $\{\dot{\xi}_{\kappa,\sigma,k}\}$, as given in Section 2 for $\mathcal{H}^r_a$ which we view as an orthonormal basis for a Euclidean (Hilbert space) norm. Similarly, $\mathcal{K}^r_a$ is the space of r-fold periodic vectors in $\mathcal{K}_{bond}$ with orthonormal basis $\{\dot{\eta}_{e,k}\}_{e\in F_e, k\in r}$.

Let $\omega_l = e^{2\pi i/r_l}$, for $l = 1, 2, 3$, let $\mathbb{T}^3_r$ be the finite discrete torus

$$\mathbb{T}^3_r = \{\omega^k = (\omega_1^{k_1}, \omega_2^{k_2}, \omega_3^{k}) : k \in r\}$$

and consider the vector space of function on $\mathbb{T}^3_r$ taking values in the column vector space $\mathbb{C}^{3|F_v|}$. This space has the same dimension as $\mathcal{K}^r_a$ since, for example, one could take a basis consisting of the basic functions

$$w \to \chi_k(\omega)\xi_{\kappa,\sigma}, \quad \kappa \in F_v, \sigma \in \{x, y, z\}, k \in r,$$

where $\chi_k : \mathbb{T}^3_r \to \mathbb{C}$ is the indicator function for the point ω^k in $\mathbb{T}^3_r$. Here the set of vectors $\{\xi_{\kappa,\sigma}\}$ is the basis for $\mathbb{C}^{3|F_v|}$. It is convenient to introduce a natural Hilbert space inner product so that the indicator functions above are orthogonal with norms $(r_1r_2r_3)^{-1/2}$. This corresponds to viewing the function space as $L^2(\mathbb{T}^3_r) \otimes \mathbb{C}^{3|F_v|}$ where $L^2(\mathbb{T}^3_r)$

has Hilbert space (Euclidean) norm determined by normalised counting measure on $\mathbb{T}_r^3$.

Similarly we introduce the function Hilbert space $L^2(\mathbb{T}_r^3) \otimes \mathbb{C}^{|F_e|}$ which has the same vector space dimension as $\mathcal{K}_b^r$.

Note now that the vectors $w^k \otimes \xi_{\kappa,\sigma}$, for $k \in r$, given explicitly as the functions

$$w \in \mathbb{T}_r^3 \to w^k \xi_{\kappa,\sigma}$$

form an orthonormal basis. This is because of the standard orthogonality of the set of vectors

$$(1, \beta^q, \beta^{2q}, \ldots, \beta^{(p-1)q}), \quad 1 \leq q \leq p,$$

where β is the p^{th} root of unity.

Thus we may define the unitary transformation

$$U_a : \mathcal{K}_a^r \to L^2(\mathbb{T}_r^3) \otimes \mathbb{C}^{3|F_v|}$$

in terms of the bijection

$$\dot{\xi}_{\kappa,\sigma,k} \to w^k \otimes \xi_{\kappa,\sigma}, \quad \kappa \in F_v, \sigma \in \{x, y, z\}, k \in r.$$

In a similar way, for the edge motif vector space there is a natural Hilbert space isomorphism

$$U_b : \mathcal{K}_b^r = \mathbb{C}^{|F_e| r_1 r_2 r_3} \to L^2(\mathbb{T}_r^3) \otimes \mathbb{C}^{|F_e|}$$

determined by a bijection between bases,

$$\dot{\eta}_{e,k} \to w^k \otimes \eta_e, \quad e \in F_e, k \in r.$$

Let $\Psi(w)$ be any complex function on $\mathbb{T}_r^3$ whose values are complex matrices of size $|F_e| \times 3|F_v|$. Then this function determines a linear transformation

$$M_\Psi : L^2(\mathbb{T}_r^3) \otimes \mathbb{C}^{3|F_v|} \to\to L^2(\mathbb{T}_r^3) \otimes \mathbb{C}^{|F_e|}$$

by pointwise matrix multiplication; for a function $F(w)$ in the domain space $(M_\psi F)(w) = \Psi(w)F(w)$. Note that one may view the transformation as being in block diagonal form since it is evidently equivalent to a block diagonal transformation with matrix

$$\sum_{\omega \in \mathbb{T}_r^3} \oplus \Phi(\omega).$$

The next proposition shows the role of $\Phi_{\mathcal{C}}(z)$ and provides a convenient representation of the rigidity matrices for supercell periodicity. In particular it provides a counting formula for the number of floppy modes associated with a supercell.

Theorem 3.3. *Let $r \in \mathbb{Z}_+^3$ and let $\Phi^r(w)$ be the function on the finite 3-torus $\mathbb{T}_r^3$ determined by the restriction of $\Phi_{\mathcal{C}}(z)$. Then*

(i) the rigidity matrix transformation $R^{(r)} : \mathcal{K}_a^r \to \mathcal{K}_b^r$ for r-periodic displacements is unitarily equivalent to the multiplication transformation M_{Φ^r}, specifically, $R^{(r)} = U_b^* M_{\Phi^r} U_a$.

(ii) the number of r-periodic floppy modes is

$$\dim\ker R^{(r)} = \dim\ker \mathcal{M}_{\Phi^r} = \sum_{k\in r} \dim\ker(\Phi_{\mathcal{C}}(\omega^k))$$

where $\omega = (exp(2\pi/r_1, \dots, exp(2\pi/r_1)$ and the sum extends over the $r_1r_2r_3$ points of the finite torus..

Proof. Let $\kappa' \in F_v, \sigma \in \{x, y, z\}$ and let $k' \in r$ and consider the expansion

$$R^{(r)}\dot{\xi}_{\kappa',\sigma,k'} = R(\mathcal{C})\dot{\xi}_{\kappa',\sigma,k'} = \sum_{e\in F_e, k\in r} \alpha_{(e,k),(\kappa',\sigma,k')}\dot{\eta}_{e,k}$$

in terms of the basis for $\mathcal{K}_b^r$. Thus the coefficients of the vectors $\dot{\eta}_{e,k}$ give the representing matrix for $R^{(r)}$, with rows labelled by the (e, k) and columns labelled by the triples (κ', σ, k'). Let $e = [p_{\kappa,\delta_1}, p_{\tau,\delta_2}]$ be an nonreflexive edge in F_e with edge vector $v_e = p_{\kappa,\delta_1} - p_{\tau,\delta_2}$. Then the translated edges $T_k e$, for $k \in r$, have the same edge vector and the entries of the rigidity matrix for row (e, k) imply that

$$\alpha_{(e,k),(\kappa,\sigma,k+\delta_1)} = (v_e)_\sigma,$$
$$\alpha_{(e,k),(\tau,\sigma,k+\delta_2)} = -(v_e)_\sigma.$$

Here $k + \delta_1$ and $k + \delta_1$ are taken modulo (the 3-tuple) r. All other coefficients for row (e, k) are equal to zero.

With respect to the natural inner product on $\mathcal{K}_b^r$ we have

$$\langle R^{(r)}\dot{\xi}_{\kappa,\sigma,k+\delta_1}, \dot{\eta}_{e,k}\rangle = (v_e)_\sigma,$$
$$\langle R^{(r)}\dot{\xi}_{\tau,\sigma,k+\delta_2}, \dot{\eta}_{e,k}\rangle = -(v_e)_\sigma,$$

with other entries of the row equal to zero. Thus, in view of the specification of U_a and U_b we have

$$\langle U_b R^{(r)} U_a^*(w^{k+\delta_1} \otimes \xi_{\kappa,\sigma}), w^k \otimes \eta_e\rangle = (v_e)_\sigma,$$
$$\langle U_b R^{(r)} U_a^*(w^{k+\delta_2} \otimes \xi_{\tau,\sigma}), w^k \otimes \eta_e\rangle = -(v_e)_\sigma.$$

With $T = U_b R^{(r)} U_a^*$ this gives

$$\langle T(w^k \otimes \xi_{\kappa,\sigma}), w^k \otimes \eta_e\rangle = \overline{\omega}^{\delta_1}(v_e)_\sigma,$$
$$\langle T(w^k \otimes \xi_{\tau,\sigma}), w^k \otimes \eta_e\rangle = -\overline{\omega}^{\delta_2}(v_e)_\sigma.$$

The case of a reflexive edge is the same except that there is at most one nonzero entry in the corresponding row, taking the form of the sum of the two values, namely $(\overline{\omega}^{\delta_1} - \overline{\omega}^{\delta_2})(v_e)_\sigma$.

One the other hand, the form of $\Phi_{\mathcal{C}}$ given in Definition 2.5 shows for nonreflexive edges

$$\langle \Phi^r(w)(w^k \otimes \xi_{\kappa,\sigma}), w^k \otimes \eta_e\rangle = \langle \Phi^r(w)(1 \otimes \xi_{\kappa,\sigma}), 1 \otimes \eta_e\rangle = \overline{\omega}^{\delta_1}(v_e)_\sigma,$$
$$\langle \Phi^r(w)(w^k \otimes \xi_{\tau,\sigma}), w^k \otimes \eta_e\rangle = \Phi^r(w)(1 \otimes \xi_{\tau,\sigma}), 1 \otimes \eta_e\rangle = -\overline{\omega}^{\delta_2}(v_e)_\sigma,$$

with a corresponding formula for a reflexive edge. Thus $R^{(r)}$ and $U_b^* M_{\Phi^r} U_a$ have the same representing matrices and so are equal and the proof of (i) and (ii) is complete. □

3.3. $\Phi_{\mathcal{C}}(z)$ **as a Hilbert space operator.** Write $\mathcal{K}_a^2$ and $\mathcal{K}_b^2$ for the Hilbert spaces of square summable sequences in $\mathcal{K}_{atom}$ and $\mathcal{K}_{bond}$. Then $R(\mathcal{C})$ determines a bounded Hilbert space operator from $\mathcal{K}_a^2$ to $\mathcal{K}_b^2$ which intertwines the shift operators as before, although now these operators are unitary operators. Identifying square-summable sequences with square integrable functions one obtains unitary equivalences between $\mathcal{K}_a^2$ and $L^2(\mathbb{T}^d) \otimes \mathbb{C}^{d|F_v|}$ and between $\mathcal{K}_b^2$ and $L^2(\mathbb{T}^d) \otimes \mathbb{C}^{|F_e|}$. With careful spatial identifications one can identify the corresponding (unitary) transform of the linear transformation $R(\mathcal{C})$ with a multiplication operator between these matrix-valued function spaces where the multiplying function is $\Phi_{\mathcal{C}}(z)$. For more details see Owen and Power [16] where other operator-theoretic considerations are indicated.

We remark that the choice of $\bar{z}$ rather than z in the Definitions 2.4, 2.5 for $\Phi(z)$ is somewhat arbitary from the perspective of translationally periodic crystal frameworks. However elsewhere we consider semi-infinite crystal frameworks and in this case it is natural to model displacement velocity sequences in the domain by analytic functions and power series, with positive powers of the variable. With this choice the negative exponent formalism of these definitions is implied and so it seems appropriate to build this in to the definition of $\Phi(z)$ at the outset.

4. Rigid unit modes.

Let $\mathcal{C} = (F_v, F_e, \mathcal{T})$ be a crystal framework in $\mathbb{R}^d$, $d = 2, 3, \dots$, with motif (F_v, F_e), full rank translation group $\mathcal{T}$ and rigidity matrix $R(\mathcal{C})$.

Definition 4.1. (i) The RUM spectrum of $\mathcal{C}$ is the set $\Omega(\mathcal{C})$ of points $\omega = (\omega_1, \dots, \omega_d)$ in $\mathbb{T}^d$ such that there is a nonzero vector u with $R(\mathcal{C})u = 0$ which is periodic modulo the phase ω;

$$\Omega(\mathcal{C}) = \{\omega \in \mathbb{T}^d : \ker R^\omega \neq \{0\}\}.$$

(ii) The mode multiplicity function defined on $\Omega(\mathcal{C})$ is given by $\mu(\omega) = \dim \ker R^\omega$.

(iii) The RUM dimension $\dim_{RUM}(\mathcal{C})$ of $\mathcal{C}$ is the real dimension of the real algebraic variety $\Omega(\mathcal{C})$.

It follows that

$$\Omega(\mathcal{C}) = \{\omega \in \mathbb{T}^d : \operatorname{rank} \Phi_{\mathcal{C}}(\omega) < d|F_v|\}$$

and in the case of frameworks in Maxwell counting equilibrium,

$$\Omega(\mathcal{C}) = \{\omega \in \mathbb{T}^d : \det \Phi_{\mathcal{C}}(\omega) = 0\}.$$

From the definitions we see that the periodic floppy modes, as we have defined them, are vectors in the nullspace of R^ω for the points ω in the rational d-torus $\mathbb{T}^d_{rat} \subseteq \mathbb{T}^d$. Also we may consider the corresponding inclusion

$$\Omega_{flop}(\mathcal{C}) := \Omega(\mathcal{C}) \cap \mathbb{T}^d_{rat} \subseteq \Omega(\mathcal{C}).$$

From the remarks at the end of Section 2.1 it follows that the RUM spectrum and the rational subset Ω_{flop} may depend on the choice of translation group, or, equivalently, on the choice of unit cell although in the notation we usually suppress this. However, we note the following simple relationship between the RUM spectrum $\Omega(\mathcal{C}, \mathcal{S})$ and the spectrum $\Omega(\mathcal{C}, \mathcal{T})$ when $\mathcal{S}$ is a subgroup of $\mathcal{T}$ corresponding to a supercell of $r_1 \times \cdots \times r_d$ unit cells. If

$$\mathcal{S} = \{T_k : r_i \text{ divides } k_i, 1 \leq i \leq d\}$$

then there is a natural covering map $\gamma : \mathbb{T}^d \to \mathbb{T}^d$ given by $\gamma(w) = (w_1^{r_1,\ldots,w_d^{r_d}}$. It follows from the definition of RUMs that

$$\Omega(\mathcal{C}, \mathcal{S}) = \gamma(\Omega(\mathcal{C}, \mathcal{T})).$$

In particular the dimension of $\Omega(\mathcal{C})$ is a property of $\mathcal{C}$ alone since the covering map is finite-to-one.

The following theorem and the ensuing discussion relate the order of floppy modes to the RUM dimension of $\mathcal{C}$.

Theorem 4.2. *(i) Let $(\mathcal{C}, \mathcal{T})$ be a d-dimensional crystal framework with RUM spectrum $\Omega(\mathcal{C}) \subseteq \mathbb{T}^d$. Then the nullity $\nu_n = \dim\ker R_n$ of the rigidity matrix for n-fold periodicity satisfies*

$$d - 1 + |\Omega(\mathcal{C}) \cap \mathbb{T}^d_r| \leq \nu_n \leq d|F_v||\Omega(\mathcal{C}) \cap \mathbb{T}^d_r|$$

where $|F_v|$ is the number of vertices in the partition unit cell and where $\mathbb{T}^d_r$ is the discrete torus for $r = (n, n, n)$.

(ii) If $\nu_n \geq cn^\alpha$ for some $c > 0, \alpha > 0$, then $\dim(\Omega(\mathcal{C})) \geq \alpha$.

Proof. (i) From Theorem 3.3 above we have

$$\nu_n = \dim\ker R_n = \sum_{k \in r} \dim\ker(\Phi_{\mathcal{C}}(\omega^k)).$$

Thus the second inequality follows readily since $\dim\ker(\Phi_{\mathcal{C}}(\omega) \leq d|F_v|$ for all ω. On the other hand, if $\omega^k \in \Omega(\mathcal{C}) \cap \mathbb{T}^d_r$ then $\dim\ker \Phi_{\mathcal{C}}(\omega^k) \geq 1$, while for wave vector $\mathbf{k} = (0, 0, 0)$ we have $\dim\ker(\Phi_{\mathcal{C}}(1, \ldots, 1)) \geq d$, since there are certainly d linearly independent translation infinitesimal flexes. Thus the first inequality follows.

(ii) follows from (i) since for any algebraic variety Ω, if the dimension is less than the integer α then the cardinality of $\Omega \cap \mathbb{T}^d_r$ is at most of order $n^{\alpha-1}$. □

Three illustrations will be given of the following corollary in Section 5, including the Roman tile framework $\mathcal{C}_{\mathrm{Rom}}$ and the sodalite framework $\mathcal{C}_{\mathrm{SOD}}$.

Corollary 4.3. *With the notation above the following assertions are equivalent for a crystal framework $\mathcal{C}$ in $\mathbb{R}^d$.*

(i) $\mathcal{C}$ has a local floppy mode.

(ii) $\nu_n \geq cn^d$, for all n, for some $c > 0$.

(iii) $\dim(\Omega(\mathcal{C})) = d$.
(iv) $\Omega(\mathcal{C}) = \mathbb{T}^d$.

Proof. The equivalence of (i) and (ii) follows from Proposition 2.10. The last theorem shows that (ii) and (iii) are equivalent, and (iii) is equivalent to (iv) since $\Omega(\mathcal{C})$ is a real algebraic variety in $\mathbb{T}^d$. □

Remark 4.4. Suppose that $\Omega(\mathcal{C})$ has dimension t with t less that d and that $\Omega(\mathcal{C})$ is *rationally parametrised* in the sense that there are rational polynomials $g_1(s), \dots, g_d(s)$, in variable $s_1, \dots, s_t$, such that

$$\Omega(\mathcal{C}) = \{(\exp(2\pi i g_1(s)), \dots, \exp(2\pi i g_d(s))) : s \in [0,1)^d\} \subseteq \mathbb{T}^d.$$

Then it follows that $\Omega_{flop}(\mathcal{C})$ is dense in $\Omega(\mathcal{C})$ and that the n-fold periodic floppy modes, which are associated with the rational points, are of order n^t. In general however, in the case of exotic RUM spectra, one should expect examples where the rational points of the RUM spectrum are not dense.

5. Crystal Frameworks.

We first show how the points of the RUM spectrum $\Omega(\mathcal{C})$ arise as the wave vectors $\mathbf{k}$ of the wave excitations of $\mathcal{C}$ which induce vanishing bond distortion in their long wavelength limits. This is followed by the determination of the RUM spectra, both standard and exotic, for a number of key frameworks. The infinitesimal flex approach here gives theoretical insights as well as alternative computational avenues and we intend to develop this further elsewhere.

5.1. **RUMs and long wavelength limits.** Suppose that $\mathcal{C}$ is a crystal framework in $\mathbb{R}^d$, with motif data $(F_v, F_e, \mathcal{T})$ and suppose that the vertices $p_{\kappa,k}$ undergo a standard wave motion,

$$p_{\kappa,k}(t) = p_{\kappa,k} + u_{\kappa,k}(t), \quad \kappa \in F_v, k \in \mathbb{Z}^d,$$

where $u_{\kappa,k}(t)$ represents the local oscillatory motion of atom κ in the translated unit cell with label $k \in \mathbb{Z}^3$. Following formula-simplifying convention, these motions are complex-valued, the case of real motion being recoverable from real an imaginary parts. (See Dove [8].) Thus we have

$$u_{\kappa,k}(t) = u_\kappa \exp(2\pi i \mathbf{k} \cdot k) \exp(i\alpha t)$$

where $\mathbf{u} = (u_\kappa)_{\kappa \in F_v}$ is a fixed vector in $\mathbb{C}^{3|F_v|}$, where $\mathbf{k}$ is the wave vector and where α is the frequency.

Considering the distortion $\Delta_e(t)$ for the edge $e = [p_{\kappa,k}, p_{\tau,k+\delta(e)}]$ we have

$$\begin{aligned}\Delta_e(t) &:= |p_{\kappa,k}(t) - p_{\tau,k+\delta(e)}(t)|^2 - |p_{\kappa,k}(0) - p_{\tau,k+\delta(e)}(0)|^2\\ &= 2Re\langle p_{\kappa,k} - p_{\tau,k+\delta(e)}, u_{\kappa,k}(t) - u_{\tau,k+\delta(e)}(t)\rangle\\ &\quad +2Re\langle p_{\kappa,k} - p_{\tau,k+\delta(e)}, u_{\kappa,k}(0) - u_{\tau,k+\delta(e)}(0)\rangle\\ &\quad +\epsilon(\mathbf{u}, \mathbf{k}, k, \alpha t)\end{aligned}$$

where

$$\epsilon(\mathbf{u},\mathbf{k},k,\alpha t) = |u_{\kappa,k}(t) - u_{k+\delta(e)}(t)|^2 - |u_{\kappa,k}(0) - u_{k+\delta(e)}(0)|^2.$$

First note that in any finite time period $[0,T]$ the difference quantities $\epsilon(\mathbf{u},\mathbf{k},k,\alpha t)$ tends to zero uniformly, for all $t \in [0,T]$ and all k in $\mathbb{Z}^3$, as the frequency α tends to zero. This follows readily from the fact that for any θ the quantity

$$|\sin(\alpha t + \theta) - \sin(\alpha t)|^2 - |\sin(\theta) - \sin(0)|^2$$

tends to zero uniformly for $t \in [0,T]$ as α tends to zero.

For the other terms for $\Delta_e(t)$ note that

$$\begin{aligned} &2Re\langle p_{\kappa,k} - p_{\tau,k+\delta(e)}, u_{\kappa,k}(t) - u_{\tau,k+\delta(e)}(t)\rangle \\ &= 2Re[e^{-\alpha t - 2\pi i \mathbf{k}\cdot k}\langle p_{\kappa,k} - p_{\tau,k+\delta(e)}, u_\kappa - \omega^{\delta(e)}u_\tau\rangle] \\ &= 2Re[e^{-\alpha t - 2\pi i \mathbf{k}\cdot k}\langle p_\kappa - p_{\tau,\delta(e)}, u_\kappa - \omega^{\delta(e)}u_\tau\rangle] \end{aligned}$$

which is zero, irrespective of t, if $(\omega^k u_\kappa)$ is an infinitesimal flex of the framework.

It follows that we have proven the implication (i) implies (ii) in the following proposition. The converse assertion follows from the same equations and so we conclude that the points in $\Omega(\mathcal{C})$ correspond to the wave vectors of RUM phonons that appear in simulations.

Theorem 5.1. *Let $\mathcal{C}$ be a crystal framework, with specified periodicity, and let $\mathbf{k}$ be a wave vector with point $\omega \in \mathbb{T}^3$. Then the following assertions are equivalent.*

(i) $(\omega^k u_\kappa)_{\kappa,k}$ is a nonzero periodic-modulo-phase infinitesimal (complex) flex for $\mathcal{C}$.

(ii) For the vertex wave motion

$$p_{\kappa,k}(t) = p_{\kappa,k} + u_\kappa \exp(2\pi i\ \mathbf{k}\cdot k)\exp(i\alpha t),$$

and a given time interval, $t \in [0,T]$, the bond length changes

$$\delta e(t) = |p_{\kappa,k}(t) - p_{\tau,k+\delta(e)}(t)| - |p_{\kappa,k}(0) - p_{\tau,k+\delta(e)}(0)|,$$

tend to zero uniformly, in t and e, as the wavelength $2\pi/\alpha$ tends to infinity.

In the last two decades the RUM spectra of frameworks associated with specific material crystals have been computed using the programme CRUSH [2]. The method here reflects principle (ii) in the proposition above and RUM identifications are obtained by lattice dynamics simulation. This is based upon a double limiting process known as the split atom method. Here each shared vertex (often an oxygen atom) is duplicated, for each rigid unit, and connected by bonds of zero length and increasing strength, tending to infinity. In this setting the RUM wave vectors coincide with those for which the long wavelength limits have vanishing energy and so can be identified and counted.

Some of the results of this approach can be found in [5], [6], [7], [4], [21].

5.2. Standard and exotic RUM spectra.

The RUM spectrum of a simple crystal framework $(\mathcal{C}, \mathcal{T})$ in three dimensions often contains or consists of a union of a finite number of points, lines and planes of wave vectors $\mathbf{k}$. In this case and in the order N case, with $\Omega(\mathcal{C}) = \mathbb{T}^3$, we say that $\Omega(\mathcal{C})$ is *standard*. Otherwise we say that the RUM spectrum is *exotic*. (In view of the arithmetic subtlety alluded to in Remark 4.4 one should view these terms as working definitions adequate for our discussion.) We shall see, for example, that the following basic crystal frameworks have standard RUM spectrum: the grid frameworks $\mathcal{C}_{\mathbb{Z}^d}$ in $\mathbb{R}^d$, the kagome framework, the kagome net framework in $\mathbb{R}^3$, and the octahedron net framework $\mathcal{C}_{\mathrm{OCT}}$ associated with perovskites and which may be viewed as a three-dimensional analogue of the squares framework $\mathcal{C}_{\mathrm{sq}}$.

The infinitesimal flex perspective that we have been pursuing can enable the prediction of lines and planes in the RUM spectrum, even without the computation of the rank degeneracies of $\Phi_{\mathcal{C}}(z)$, as we now indicate.

Consider, for example, the basic grid framework $\mathcal{C}_{\mathbb{Z}^2}$ in the plane, as indicated in Section 2 but re-orientated so that the vertices are the points with integer coordinates and the translation group is that for integer translations. (The motif has a single vertex, $F_v = \{p_\kappa\}$, and two edges.) Examining all edges it becomes evident that there exists an infinitesimal flex u supported on the x-axis, with $u_{\kappa,(k_1,0)} = (1, 0)$ for all $k_1 \in \mathbb{Z}$. Using all the parallel translates $T_{(0,k_2)}u$ of u, we may define the periodic-modulo-phase displacement v given by

$$v = \sum_{k_2 \in \mathbb{Z}} \omega_2^{k_2} T_{(0,k_2)} u,$$

where ω_2 is a fixed point in $\mathbb{T}$. Then v is well-defined and is a nonzero infinitesimal flex and so its phase $(1, \omega_2)$ in $\mathbb{T}^2$ lies in the RUM spectrum. In the language of wave vectors we see that the RUM spectrum contains the line of wave vectors $(0, \alpha)$. By symmetry the line $(\alpha, 0)$ is also included. Similar arguments apply to the kagome lattice which also has linearly localised infinitesimal flexes.

There is a general principle at work here which holds, as we illustrate below, for a crystal framework $\mathcal{C}$ which has an infinitesimal flex u which is

(a) *band limited*, in the sense of being supported by a set of framework vertices within a finite distance of a direction axis for $\mathcal{T}$, and

(b) periodic for the direction axis direction.

Indeed, by (a) one can form a sum analogous to that above, using the complementary direction axis, to obtain a well-defined periodic-modulo-phase infinitesimal displacement. By linearity, and commutation of the rigidity matrix with translations, v is an infinitesimal flex. Similarly, if (b) is changed to the requirement of unidirectional phase-periodicity for phase ω_1 then we deduce that $\omega_1 \times \mathbb{T}$ is contained in the RUM spectrum.

Similarly one can construct phase-periodic flexes for the grid framework in three dimensions and higher. For the grid framework $\mathcal{C}_{\mathbb{Z}^2}$ in three dimensions one deduces from the evident line-localised infinitesimal flexes that there are three surfaces, $z = 1$, $w = 1$ and $u = 1$, in $\Omega(\mathcal{C}_{\mathbb{Z}^3})$. Their union in fact forms the entire RUM spectrum of the grid framework, since the form of the matrix function (for the single vertex motifs) is diagonal with entries $1 - z, 1 - w, 1 - u$. However the point we underline here is that a line-localised periodic flex leads directly to a hyperplane of wave vectors in the RUM spectrum.

Similar observations hold in three dimensions for plane-localised flexes. In three dimensions, for example, such a flex, which is assumed to be "in-plane phase-periodic", leads to a line of RUM wave vectors. This in the case for the framework for perovskite in Example (h) below.

In the case of exotic RUMs a diversity of examples are implied by recent experimental and simulation studies in material science. (See in particular Dove et al [4].) We now note that the matrix function perspective also leads to the expectation that the set of RUMs of a "typical" material crystal is likely to be exotic.

In view of Theorem 5.1, Proposition 3.1 and Definitions 2.5, 4.1 the low energy vibrational RUM spectrum of a crystal framework formed by a 3d zeolite will be approximated by the zero set, on the 3-torus, of the three-variable polynomial $p_{\mathcal{C}}(z)$ of the framework. If the edge motif set F_e has n edges with an "external" vertex not in F_v then this polynomial is "likely" to have degree n. At one extreme, this fails if there exist localised flexes, since then the polynomial vanishes identically and at another extreme, in the absence of symmetry for example, the polynomial may fail to have any zeros on the torus, apart from the point $(1, 1, 1)$ which is ever-present in view of the acoustic/translational modes. However, away from these extremes there will be generally be RUMs arising from the surfaces and curves of intersection defined by irreducible factors of $p_{\mathcal{C}}(z)$. Linear factors create planes and lines and (roughly speaking) one expects that for complex crystals that there will not be a full linear factorisation of the crystal polynomial and that some of the nonlinear factors will contribute RUMs. This was confirmed by Wegner [22] in the case of the framework for the HP tridymite phase of SiO_2 for example. We give another explicit exotic factorisation below for a two-dimensional zeolite.

5.3. **The RUM spectra of crystal frameworks.** The following definition is convenient.

Definition 5.2. A mathematical zeolite in two (resp. three) dimensions is a crystal framework $\mathcal{C}$ in the plane (resp. $\mathbb{R}^3$) consisting of congruent triangles (resp. congruent tetrahedra), each pair of which intersect disjointly or at a common vertex, or edge, or face, and such that every vertex is shared by two triangles (resp. tetrahedra).

One can view the frameworks of material and mathematical zeolites at the databases [23], [24] respectively. Of particular interest are the material zeolites, which are denoted by an upper case triple, such as FAU, PAU, SOD, RWY, ... , these often being a mnemonic for a material group indicator (faujasite, paulingite, sodalite, ..., etc.). We write $\mathcal{C}_{\mathrm{XYZ}}$ for the mathematical zeolite framework associated with the material zeolite XYZ when the geometry is unequivocal, as is the case for the cubic form of SOD for example (see below). Note that while the databases often highlight the framework formed by "T atoms" at the tetrahedral centres (each being 4-coordinated with neighbour T atoms), we identify the tetrahedral net framework, corresponding to O atoms as vertices.

Example (a): The regular 4-ring framework. A fundamental $2d$ zeolite $\mathcal{C}_a$ is determined by the four-pointed star indicated in Figure 4. It is an instructive example in that it is sufficiently simple that one can deduce its RUM spectrum and also its polynomial $p_{\mathcal{C}_a}(z, w)$ from infinitesimal arguments, by the band-limited arguments outlined in Section 5.2.

Note that there are four non-internal edges in the motif and so four rows of $\Phi_{\mathcal{C}}(z, w)$ will carry monomials. Thus $p_{\mathcal{C}}(z, w)$ has total degree at most 4. One can show that there are infinitesimal flexes of the finite subframeworks as indicated in Figures 3 and 4. The top and bottom vertices of each are fixed by the flex. Each flex extends by horizontal periodicity to a band-limited infinitesimal flex. In the former case there is two step horizontal periodicity while in the latter case there is strict horizontal periodicity although the band is two cells wide.



FIGURE 3. A 2-cell periodic band-limited flex of $\mathcal{C}_a$.



FIGURE 4. A 1-cell periodic band-limited flex of $\mathcal{C}_a$.

From the discussion in Section 5.2 the first band-limited flex shows that $(-1,\omega_2) \in \Omega(\mathcal{C})$ for all $\omega_2 \in \mathbb{T}$. By symmetry $(\omega_1,-1) \in \Omega(\mathcal{C})$ for all $\omega_1 \in \mathbb{T}$. Thus $\Omega(\mathcal{C})$ contains the set

$$(\{1\} \times \mathbb{T}) \cup (\mathbb{T} \times \{1\}) \cup (\{-1\} \times \mathbb{T}) \cup (\mathbb{T} \times \{-1\}).$$

It follows that $p_{\mathcal{C}}(z,w)$ is divisible by the irreducible factors $z-1, w-1, z+1, w+1$. Since $p_{\mathcal{C}}(z,w)$ has total degree at most 4 it follows that either p vanished identically or

$$p_{\mathcal{C}}(z,w) = (z-1)(w-1)(z+1)(w+1).$$

Finally, note that former case does not hold. One can see this, thematically, by demonstrating that there are no local flexes. Alternatively one may simply compute $\det \Phi(1/3,1/3) \neq 0$. Thus the RUM spectrum is precisely the fourfold union above.

Examples (b), (c): Deformation phases of C_a. The regular 4-ring framework $\mathcal{C}_a$ has a finite flex deformation, or phase transition, to a companion frameworks $\mathcal{C}_b$ in which each 8-ring of triangles borders a regular octahedron. We call $\mathcal{C}_b$ the regular 8-ring framework. A motif for the natural translation group is formed by an 8-ring of 24 edges with four boundary vertices omitted. See Figure 5. There are 8 edges with external vertices and so the expectation is that $p_{\mathcal{C}_b}(z,w)$ has degree 8 and this is the case. In particular it follows, from Corollary 4.3 for example, that there are no localised RUMs anywhere in the infinite framework. No apparent band-limited infinitesimal flexes are present in this framework and indeed numerical calculation shows that there are no lines of wave vectors and that the RUM spectrum is exotic, consisting of four closed disjoint curves on $\mathbb{T}^2$ meeting at $(1,1,1)$.



FIGURE 5. Deformations of $\mathcal{C}_a$, with angle $10\pi/12$ for $\mathcal{C}_c$, angle $9\pi/12$ for $\mathcal{C}_b$ (in an offset position), angle $8\pi/12$ for $\mathcal{C}_a$, rotated by $\pi/4$, and angle $7\pi/12$, for $\mathcal{C}_b$, the regular 8-ring framework.

While the matrix-function $\Phi_{\mathcal{C}_b}(z)$ is rather large, with 24 rows and columns, it is sparse and its entries may be conveniently normalised by dividing each row by the magnitude of the x-coordinate difference. The magnitudes of the nonzero nonunit entries of the resulting matrix are then the tangents of the angles $k\pi/24$, for $k = 1, 3, 5, 7, 9, 11$, all of which lie in the field extension $\mathbb{Q}(\sqrt{2}, \sqrt{3})$. It can be shown that

$$p_{\mathcal{C}_b}(z,w) = z^4w^2 + z^2w^4 - 2\sqrt{3}(z^3w^3 + z^3w + w^3z + zw) +$$
$$(4\sqrt{3}-4)(z^3w^2 + z^2w^3 - 2z^2w^2 + z^2w + zw^2) + w^2 + z^2.$$

and that this polynomial admits an explicit factorisation as a product

$$p_{\mathcal{C}_b}(z,w) = p_1(z,w)p_2(z,w)$$

where

$$p_1(z,w) = z^2w - (\sqrt{3}+\sqrt{2})zw^2 + 2(\sqrt{3}+\sqrt{2}-1)zw - (\sqrt{3}+\sqrt{2})z + w,$$
$$p_2(z,w) = z^2w - (\sqrt{3}-\sqrt{2})zw^2 + 2(\sqrt{3}-\sqrt{2}-1)zw - (\sqrt{3}-\sqrt{2})z + w.$$

Each of the factors is responsible for two of the four closed curves that comprise $\Omega(\mathcal{C}_b)$ which is illustrated in Figure 6.



FIGURE 6. The curved wave vector spectrum of $\mathcal{C}_b$.

This approach leads to a rigourous algebraic determination of the exotic RUM spectrum but it is nevertheless of interest to obtain a more intuitive understanding of such curves and their modes. One approach to this is in terms of *RUM spectrum evolution* which we now sketch.

Figure 5 indicates four frameworks, say $\mathcal{C}_1, \mathcal{C}_2, \mathcal{C}_3, \mathcal{C}_4$, determined by their unit cells. These frameworks are snapshots in a continuous smooth path, or deformation, $t \to \mathcal{C}_t$ from $\mathcal{C}_1 = \mathcal{C}_c$ to $\mathcal{C}_4 = \mathcal{C}_b$ which is driven by the indicated angle. The angle starts at $10\pi/12$ and decreases to $7\pi/12$, the other snapshots being for $9\pi/12$ and $8\pi/12$. Notice that $\mathcal{C}_2$ is a diagonal translate of $\mathcal{C}_r$ and that $\mathcal{C}_3$ is a rotation of $\mathcal{C}_a$ by $\pi/4$. These frameworks are endowed with the natural isometry group generated by horizontal and vertical motions, with differing period vectors.

We have seen the RUM spectrum of $\mathcal{C}_3$ in Example (a). However, here the unit cell is doubled and is rotated by $\pi/4$. Accordingly the new RUM spectrum is determined as the image of the old one under the "doubling map" $(w_1, w_2) \to (w_1^2, w_2^2)$, followed by axial rotation. It follows that

$$\Omega(\mathcal{C}_3) = \{(w, w), (w, -w) : w \in \mathbb{T}\}.$$

In terms of reduced wave vectors this corresponds to the subset of the unit square $[0, 1)^2$ given as the union of the two diagonals.

On the other hand one can show, by infinitesimal analysis, or by numerical calculation that $\Omega(\mathcal{C}_1)$ is standard and, in terms of wave vectors, is simply the subset of the unit square $[0, 1)^2$ given as the union of the axes. We can now view the RUM spectrum of the regular 8-ring framework $\mathcal{C}_2$ as one picture in a path of sets from the axial set $\Omega(\mathcal{C}_1)$ to the cross diagonals set $\Omega(\mathcal{C}_3)$. Indeed the path of spectra $t \to \Omega(\mathcal{C}_t)$, which we refer to as a *RUM evolution*, is the path of zero sets of a path of polynomials and can be analysed in such terms.

Example (d): A 2d zeolite with order N. Figure 7 shows the unit cell for a $2d$ zeolite in which there are six framework vertices on the boundary. One can verify that there is a nonzero infinitesimal flex of the enclosed finite framework with zero displacements at the boundary vertices and a vertical displacement at the central vertex. Thus the framework has a local RUM and the RUM spectrum is all of $\mathbb{T}^2$.

In general it need not be the case that an order N crystal framework has a local RUM internal to the unit cell. This is the case for the Roman tile framework for example. Also here one could take a new unit cell in which the central vertex is shifted to the boundary and in this case one has to consider a threefold supercell before a local RUM appears.



Figure 7. Unit cell for a $2d$ zeolite with order N.

Numerical calculation shows that the mode multiplicity function takes the following values on $\mathbb{T} \times \mathbb{T}$;

$$\nu(1,1) = 4, \quad \nu(1,w) = 3, \quad \text{for } w \neq 1, \quad \nu(w,1) = 2, \text{ for } w \neq 1,$$

$$\nu(-1,w) = 2, \text{ and } \quad \nu(w_1,w_2) = 1 \text{ otherwise.}$$

In particular the RUM spectrum is standard and so also amenable to analysis in terms of band-limited flexes.

Example (e): Roman tiling framework. The next figure shows part of a two-dimensional framework $\mathcal{C}_{\text{Rom}}$ which derives from a classical Roman tiling of the plane by regular triangles, squares and hexagons. Here the triangles are the rigid units of the framework. Also the framework is 4-regular and so in particular $\mathcal{C}_{\text{Rom}}$ is in Maxwell counting equilibrium. The matrix function for a motif associated with a unit cell parallelogram enclosing six vertices is a 12 by 12 matrix in two variables.

The framework evidently has many infinitesimal flexes. Indeed for each linear square-hexagon channel there is an (edge-length-preserving) smooth deformation $(p_{\kappa,k}(t))$ in which the channel undergoes parallel collapse. Such a motion gives an infinitesimal flex $u = (p'_{\kappa,k}(0))$. More



FIGURE 8. Roman tiling framework, with order N.

apt to our discussion is the strictly periodic (phase $(1,1)$) infinitesimal flex in which each triangle undergoes identical infinitesimal rotation about its centre.

Less evident perhaps are the localised infinitesimal flexes which are supported in a finite region. Indeed there is an interesting minimal such flex u which is zero outside a 2-fold supercell (of four parallelograms) and which imparts an infinitesimal clockwise "hexagonal motion" on a ring of six triangles in this supercell. It follows that $\mathcal{C}_{\mathrm{Rom}}$ is of order N with full RUM spectrum and that the crystal polynomial is identically zero.

Curiously, despite the multi-deformability of the framework, the mode multiplicity function $\mu : \Omega(\mathcal{C}_{\mathrm{Rom}}) \to \mathbb{Z}_+$ is simply given by $\mu(1,1) = 2$ and $\mu(\omega) = 1$ for $\omega \neq (1,1)$. Equivalently, in terms of the rigid unit mode wave excitations indicated in the next section, for the zero wave vector there is simply the two-dimensional space of trivial translation (acoustic) modes, while for each other wave vector there is a single rigid unit mode. This mode, say for wave vector $\mathbf{k} = (k_1, k_2)$ in $[0,1) \times [0,1)$, corresponds to the infinitesimal flex v derived from u in terms of the well-defined ("slightly overlapping") infinite sum

$$v = \sum_{(p,q)\in\mathbb{Z}^2} e^{2\pi i(pk_1+qk_2)} T_{(p,q)} u.$$

Example (f): β-cristobalite. The so-called *kagome net* framework in three dimensions may be constructed in a layered manner as follows. Place upward tetrahedra on alternate triangles of the two-dimensional kagome framework $\mathcal{C}_{\mathrm{kag}}$ and place downward tetrahedra on the other triangles to create a framework layer. Such layers are then fused together to fill space, creating the crystal framework we denote as $\mathcal{C}_{\mathrm{knet}}$.

Note first that the band-limited periodic infinitesimal flex arguments above can be applied to the two-dimensional kagome framework, just as in Example (a), to arrive at its polynomial directly;

$$p_{kag}(z,w) = (z-1)(w-1)(z-w).$$

Note that a phase-periodic flex of the $2d$ framework, with phase (ω_1, ω_2) say, induces "layer-limited" infinitesimal flexes of the kagome net framework which are $\mathbb{Z}^2$ phase-periodic. It follows from the discussion in Section 5.2 that for all $\omega \in \mathbb{T}$ there is a rigid unit mode u of $\mathcal{C}_{\text{knet}}$ with phase $(\omega_1, \omega_2, \omega)$. Similar assertions hold for the other axial planes. Any natural motif giving rise to the crystal polynomial $p_{knet}(z,w,u)$ shows that it has total degree at most 6. Since our arguments show that it must vanish on the six planes $z-1=0, w-1=0, u-1=0, z-w=0, w-u=0, z-u=0$ it follows that

$$p_{knet}(z,w,u) = (z-1)(w-1)(u-1)(z-w)(w-u)(z-u),$$

for the monomial order with $z > w > u$.

The polynomial above was also obtained in [22] and [16] by calculation. The framework is also the tetrahedral net framework for β-cristobalite, [4] (and also happens to be associated with the recent material HerbertSmithite).

We remark that the kagome net has other deformations, or phases, and one such phase features in tridymite which was the first system where curved surfaces of RUMs were observed [4].

Note that any $2d$ zeolite $\mathcal{C}$ which admits a two-colouring, with no like coloured triangles adjacent, similarly determines a $3d$ zeolite $\mathcal{D}$ by the layer construction. In particular this applies to $\mathcal{C}_a$ and its phases $\mathcal{C}_b, \mathcal{C}_c$. Once again since the layers are effectively decoupled a RUM phase (ω_2, ω_2) for $\mathcal{C}$ leads to a line $(\omega_2, \omega_2, \omega)$ in the RUM spectrum of $\mathcal{D}$.

Example (g): Sodalite. We now define the sodalite framework $\mathcal{C}_{\text{SOD}}$ which is a zeolite framework in three dimensions, with cubic symmetry, which is built from 4-rings of tetrahedra. (The tetrahedra represent SiO_4 rigid units with silicon atoms at the centres and oxygen atoms at the vertices.) These 4-rings, so-called secondary building units in zeolite assembly [23], are oriented in the high symmetry arrangement indicated in Figure 9. Six such rings may be placed on the the six faces of an imaginary cube so that vertices sit on the midpoints of the edges of the cube. This gives a finite bar-joint framework that we call the sodalite cage. With unit edge length for the tetrahedra the cube has sidelength $1+\sqrt{2}$ while the unit cell for $\mathcal{C}_{\text{SOD}}$ has side-length $2+\sqrt{2}$.

A motif for the framework can be based on the set F_e of edges in three pairwise-connected 4-rings of the sodalite cage. The images of the edges of F_e under the action of the associated isometry group $\mathcal{T}$, with orthogonal period vectors of length $2+\sqrt{2}$ are disjoint and generate the crystal framework $\mathcal{C}_{\text{SOD}}$. For the set F_v one could take the vertices F_e except for the 12 vertices furthest from the imaginary cube faces.

There are 24 such edges and the resulting matrix function has 72 rows and 72 columns.



FIGURE 9. The top 4-ring of the sodalite cage.

We prove that $\mathcal{C}_{\mathrm{SOD}}$ is of order N. Specifically we show, by infinitesimal flex geometry, that there is a nonzero infinitesimal flex v of the finite sodalite cage framework such that all the outer vertices are fixed by v. That is, $v_{\kappa,\delta} = 0$ if $p_{\kappa,\delta}$ is an outer vertex of the cage. The "outer fixed" sodalite cage framework has 36 free vertices with 108 degrees of freedom while there are 144 constraining edges. Despite this considerable over-constraint there is sufficient symmetry to allow in a one-dimensional space of infinitesimal flexes.

We show below that an individual 4-ring, R_1 say, of the sodalite cage has an infinitesimal flex, $v^{(1)}$ say, which fixes the quadruple of outer vertices (the upper vertices in Figure 9.) In this flex the mirror quadruple vertices have equal magnitude displacement vectors which are directed towards two opposing corners of the imaginary cube. See Figure 9. Taking $v^{(1)}$ so that these vectors have magnitude 1 it follows that $v^{(1)}$ is determined up to sign and that this sign may be specified by labeling the cube corners "a" and "r" for their attracting and repelling sense. Note that one can label the eight corners of the imaginary cube in this manner so that no like labels are adjacent. In this case the implied flexes $v^{(1)}, \dots, v^{(6)}$ of the six 4 rings of the sodalite cage have equal displacement vectors at common vertices. This consistency show that there is an infinitesimal flex of the entire sodalite cage in which the outer vertices are fixed, as required.

It remains only to show that there is the stated flex of the 4-ring R_1 One can confirm this by computation or, more revealingly and thematically, by the following simple symmetric infinitesimal flex argument.

Let p_1, p_2 be two non-opposite top vertices of R_1 with intermediate vertex p_3, let p_1, p_3, p_4 be the vertices of an inward facing face of a tetrahedron of R_1 with vertices p_1, p_3, p_4, p_5, so that the lower vertex p_5 is a cube-edge midpoint. There is a unique (oblique) "upward" displacement velocity u_3 of the intermediate vertex p_3 which has unit length and is such $(u_1, u_2, u_3) = (0, 0, u_3)$ is a flex for the two edges $[p_1, p_3], [p_3, p_2]$. The displacement vector u_3 induces a unique displacement vector u_5 which is in the direction of the cube edge and is such that

$$\langle u_5 - u_3, p_5 - p_3, \rangle = 0.$$

The triple $u_1 = 0, u_3$ and u_5 now determine the infinitesimal motion of the tetrahedron, with flex vector u_4 for p_4. However, the reversal (sign change) of u_3 induces the reversal of u_5 so it is clear from the symmetric position of the tetrahedron that u_4 must be the unique unit norm (oblique) downward flex at p_4. Continuing around the ring it follows that R_1 has the desired infinitesimal flex.

One can apply similar arguments to other zeolite frameworks and of course to any such frameworks that contain a sodalite cage. Also we note, as do Kapko et al [12], that $\mathcal{C}_{\mathrm{RWY}}$ is derived from $\mathcal{C}_{\mathrm{SOD}}$ simply by replacing each tetrahedron by a rigid unit of four tetrahedra. Thus the same infinitesimal flex geometry applies and $\mathcal{C}_{\mathrm{RWY}}$ has order N.

Example (h): Perovskite. Let $\mathcal{C}_{\mathrm{OCT}}$ be the crystal framework formed by corner linked octahedra in maximal symmetry arrangement. More precisely, $\mathcal{C}_{\mathrm{OCT}}$ has the integer translation group $\mathcal{T}$ and motif (F_v, F_e) where

$$F_v = \{0, 1/2, 1/2), (1/2, 0, 1/2), (1/2, 1/2, 0)\} = \{p_{\kappa,0} : 1 \leq \kappa \leq 3\}$$

and F_e consists of the twelve framework edges between the centres of adjacent faces of the unit cell $[0, 1)^3$. Thus the vertices of $V(F_e)\backslash F_v$ have the form p_{i,γ_i}, where $\gamma_1 = (1, 0, 0), \gamma_2 = (0, 1, 0), \gamma_3 = (0, 0, 1)$.

The framework is not in Maxwell counting equilibrium, being overconstrained, but has considerable symmetry. The frameworks feature in cubic perovskites, such as SiTO_3, and RUM distributions have been determined experimentally [5], [4]. To derive $\Omega(\mathcal{C}_{\mathrm{OCT}})$ analytically by flex analysis we first obtain $\Omega(\mathcal{C}_{\mathrm{sq}})$, since the square lattice appears in two dimensional cross-sections for the three axial directions.

Performing row operations on $\Phi_{\mathcal{C}_{\mathrm{sq}}}$, as given in Section 2, we see that $(\overline{z}, \overline{w})$ is a point of the RUM spectrum if and only if the equivalent matrix

$$\Psi(z, w) = \begin{bmatrix} 1 & -1 & -1 & 1 \\ 0 & -2 & z-1 & z+1 \\ 0 & 0 & 1-wz & 1-wz \\ 0 & 0 & 0 & -2z+2w \\ 0 & 0 & -2+2z & 2-2z \end{bmatrix}$$

has rank less than 4. This occurs if and only if

$$\begin{bmatrix} 1-wz & 1-wz \\ 0 & -2z+2w \\ -2+2z & 2-2z \end{bmatrix}$$

has rank equal to 0 or 1. The rank is 0 if and only if $z = w = 1$, corresponding to the two-dimensional space of rigid motions (translational infinitesimal flexes) with phase $(1, 1)$, and the rank is 1 if and only if $z = w = -1$. Thus

$$\Omega(\mathcal{C}_{\rm sq}) = \{(1, 1), (-1, -1)\}.$$

The infinitesimal flex for the phase $(-1, -1)$ is the one for which the rigid units, in this case squares with diagonals, rotate infinitesimally in alternating senses.

Note now that this alternating rotation flex of $\mathcal{C}_{\rm sq}$ induces a plane-localised flex of $\mathcal{C}_{\rm OCT}$ in each of the framework planes $x = 1/2, y = 1/2, z = 1/2$. By the argument in Section 5 it follows that $\Omega(\mathcal{C}_{\rm OCT})$ contains the three sets of phases,

$$\mathbb{T} \times \{-1\} \times \{-1\}, \quad \{-1\} \times \mathbb{T} \times \{-1\}. \quad \{-1\} \times \{-1\} \times \mathbb{T}.$$

That the spectrum is no more than the union of these sets and the singleton $(1, 1, 1)$ can be seen from a row analysis of the 12 by 9 function matrix $\Phi_{\mathcal{C}_{\rm OCT}}(z)$ in the same style as the argument for $\mathcal{C}_{\rm sq}$. Thus, in wave vector formalism, the RUM spectrum of the octahedral net $\mathcal{C}_{\rm OCT}$ is the set of lines

$$(\alpha, 1/2, 1/2), \quad (1/2, \alpha, 1/2), \quad (1/2, 1/2, \alpha)$$

together with the acoustic wave vector $(0, 0, 0)$.

References

[1] C.S. Borcea and I. Streinu, Periodic frameworks and flexibility, Proc. R. Soc. A, doi:10.1098/rspa.2009.0676.

[2] CRUSH: The rigid unit mode program, http://www.esc.cam.ac.uk/rums/

[3] D. Cox, J. Little, D. O'Shea, Ideals, Varieties and Algorithms, Springer-Verlag, 1992.

[4] M. T. Dove, A. K. A. Pryde, V. Heine and K. D. Hammonds. Exotic distributions of rigid unit modes in the reciprocal spaces of framework aluminosilicates, J. Phys., Condens. Matter 19 (2007) doi:10.1088/0953-8984/19/27/275209.

[5] A. P. Giddy, M.T. Dove, G.S. Pawley, V. Heine, The determination of rigid unit modes as potential soft modes for displacive phase transitions in framework crystal structures. Acta Crystallogr., A49 (1993), 697 - 703.

[6] K.D. Hammonds, H. Deng, V. Heine, and M.T. Dove, How floppy modes give rise to adsorption sites in zeolites, PRL 1997

[7] K.D. Hammonds, V. Heine, and M.T. Dove, Rigid-Unit Modesand the quantitative determination of the flexibility possessed by zeolite frameworks, J. Phys. Chem. 102 (1998), 1759-1767.

[8] M. T. Dove, Introduction to lattice dynamics, Cambridge topics in Mineral Physics and Chemistry, C.U.P., 1993.

[9] P.W. Fowler and S.D. Guest, A symmetry extension of Maxwell's rule for rigidity of frames, International Journal of Solids and Structures 37 (2000), 1793 - 1804.

[10] S. D. Guest and J. W. Hutchinson, On the determinacy of repetitive structures, Journal of the Mechanics and Physics of Solids, 51 (2003), 383 - 391.

[11] R. G. Hutchinson and N. A. Fleck, The structural performance of the periodic truss, Journal of the Mechanics and Physics of Solids, 54 (2006) 756-782.

[12] V. Kapko, C. Dawson, M. M. J. Treacy and M. F. Thorpe, Flexibility of ideal zeolite frameworks, Physical Chemistry Chemical Physics, DOI: 10.1039/c003977b.

[13] J. Malesteina and L. Theran, Generic combinatorial rigidity of periodic frameworks, ArXiv, 2010.

[14] J. C. Owen and S. C. Power, Infinite bar-joint frameworks, Proceedings of the Symposium in Applied Computing, (SAC 2009) March 8-12, 2009, Honolulu, Hawaii, U.S.A.

[15] J. C. Owen and S. C. Power, Frameworks, symmetry and rigidity, Inter. J. Computational Geometry and Applications, 20, (2010), 723-750.

[16] J. C. Owen and S. C. Power, Infinite bar-joint frameworks, crystals and operator theory, ArXiv 2010.

[17] S. C. Power, Crystal frameworks, symmetry and affinely periodic flexes, preprint, in preparation.

[18] S. C. Power, Summary of the London Mathematical Society Workshop on *The Rigidity of Frameworks and Applications*, http://www.maths.lancs.ac.uk/∼power/LancRigidFrameworks.htm.

[19] E. Ross, B. Shulze and W. Whiteley, Finite motions from periodic frameworks with added symmetry, ArXiv, 2010.

[20] B. Schulze, Block-diagonalised rigidity matrices of symmetric frameworks and applications, preprint 2009, arXiv:0906.3377.

[21] I. P Swainson and M.T. Dove, Low-frequency floppy modes in β-cristobalite, Phys. Rev. Letters, 71 (1993), 193-196.

[22] F. Wegner, Rigid-unit modes in tetrahedral crystals, Journal of Physics: Condensed Matter, Volume 19, Issue 40, (2007).

[23] Zeolite database: http://www.iza-structure.org/databases/

[24] Hypothetical zeolite database: http://www.hypotheticalzeolites.net/

Dept. Math. Stats., Lancaster University, Lancaster LA1 4YF, U.K.
E-mail address: `s.power@lancaster.ac.uk`